

(72610Z) Walgreens - Tractor [Walgreens - Tractor] 136A624308

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

📥 Wear

Bearing wear is indicated.

Contamination

Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

AL)				Jun2024		
SAMPLE INFOR	<u>MATION</u>	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0119076		
Sample Date		Client Info		18 Jun 2024		
Machine Age	hrs	Client Info		20907		
Dil Age	hrs	Client Info		20907		
Oil Changed		Client Info		N/A		
Sample Status				ABNORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Nater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
ron		ASTM D5185m	>80	36		
Chromium	ppm ppm	ASTM D5185m		2		
Nickel	ppm	ASTM D5185m	>2	3		
Titanium	ppm	ASTM D5185m	~_	0		
Silver	ppm	ASTM D5185m	>3	1		
Aluminum	ppm	ASTM D5185m		35		
_ead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m		<u> </u>		
Tin	ppm	ASTM D5185m	>5	<u> </u>		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	47		
Barium	ppm	ASTM D5185m	0	0		
Volybdenum	ppm	ASTM D5185m	50	52		
Vanganese	ppm	ASTM D5185m		4		
Vagnesium	ppm	ASTM D5185m	950	549		
Calcium	ppm	ASTM D5185m	1050	1622		
Phosphorus	ppm	ASTM D5185m	995	717		
Zinc	ppm	ASTM D5185m	1180	853		
Sulfur	ppm	ASTM D5185m	2600	2512		
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	7		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	109		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4		
Nitration	Abs/cm	*ASTM D7624		8.2		
Sulfation	Abs/.1mm	*ASTM D7415		21.9		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Dxidation	Abs/.1mm	*ASTM D7414	>25	20.7		
- Maalon	11001.111111	10110/114	~	20.1		




WEAR

Sample Rating Trend



OIL ANALYSIS REPORT



Report Id: TSV1361 [WUSCAR] 06216716 (Generated: 06/24/2024 11:29:27) Rev: 1

Submitted By: Mike Hurda