




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id

**413001**

Component

**Diesel Engine**

Fluid

**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0093467</b>	GFL0093445	GFL0093508
Sample Date	Client Info		<b>20 Jun 2024</b>	30 May 2024	24 May 2024
Machine Age	hrs	Client Info	<b>4235</b>	4116	4038
Oil Age	hrs	Client Info	<b>119</b>	602	524
Oil Changed	Client Info		<b>Not Changed</b>	Changed	Not Changed
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	<b>3</b>	9	9
Chromium	ppm	ASTM D5185m >20	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m >4	<b>0</b>	<1	1
Titanium	ppm	ASTM D5185m	<b>7</b>	8	8
Silver	ppm	ASTM D5185m >3	<b>0</b>	0	<1
Aluminum	ppm	ASTM D5185m >20	<b>2</b>	5	5
Lead	ppm	ASTM D5185m >40	<b>0</b>	0	<1
Copper	ppm	ASTM D5185m >330	<b>&lt;1</b>	1	<1
Tin	ppm	ASTM D5185m >15	<b>0</b>	1	1
Vanadium	ppm	ASTM D5185m	<b>&lt;1</b>	0	<1
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>8</b>	7	7
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m 60	<b>55</b>	54	55
Manganese	ppm	ASTM D5185m 0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m 1010	<b>992</b>	934	926
Calcium	ppm	ASTM D5185m 1070	<b>1220</b>	1120	1142
Phosphorus	ppm	ASTM D5185m 1150	<b>1096</b>	1032	1049
Zinc	ppm	ASTM D5185m 1270	<b>1367</b>	1258	1261
Sulfur	ppm	ASTM D5185m 2060	<b>3883</b>	3313	3424

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>4</b>	5	5
Sodium	ppm	ASTM D5185m	<b>1</b>	4	4
Potassium	ppm	ASTM D5185m >20	<b>3</b>	8	10

## INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	<b>0.1</b>	0.4	0.3
Nitration	Abs/cm	*ASTM D7624 >20	<b>5.8</b>	8.6	8.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>18.3</b>	20.0	19.7


## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>14.2</b>	16.7	16.1
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>8.8</b>	6.9	7.7




# OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	13.7

## GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
 Sample No. : GFL0093467  
 Lab Number : 06217977  
 Unique Number : 11096174  
 Test Package : FLEET

Received : 24 Jun 2024  
 Tested : 25 Jun 2024  
 Diagnosed : 25 Jun 2024 - Wes Davis

GFL Environmental - 891 - Oklahoma City Hauling  
 1001 South Rockwell  
 Oklahoma City, OK  
 US 73128

Contact: Andy Smith  
 andrew.smith@gflenv.com

T: (405)306-1651

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)