


# **OIL ANALYSIS REPORT**

## Sample Rating Trend



Area

# (P1090072) Preferred Service-Tractor [Preferred Service-Tractor] 192A32009B

**Diesel Engine** 

PETRO CANADA DURON UHP 5W30 (36 QTS)

# DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Woor

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil


### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


TS)		No	2023	Feb 2024 Jun 20	24	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0126904	PCA0116689	PCA0109410
Sample Date		Client Info		17 Jun 2024	18 Feb 2024	02 Nov 2023
Machine Age	mls	Client Info		234842	216514	200491
Oil Age	mls	Client Info		18299	200491	21070
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	35	59	28
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>25	5	6	3
Lead	ppm	ASTM D5185m	>40	2	4	3
Copper	ppm	ASTM D5185m	>330	7	5	4
Tin	ppm	ASTM D5185m	>15	<1	2	1
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		0	<1	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	13	15	11
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	64	61	63	60
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1160	1234	1148	1084
Calcium	ppm	ASTM D5185m	820	959	934	873
Phosphorus	ppm	ASTM D5185m	1160	1120	1113	997
Zinc	ppm	ASTM D5185m	1260	1428	1301	1252
Sulfur	ppm	ASTM D5185m	3000	3920	3370	3261
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	7	7
Sodium	ppm	ASTM D5185m		4	5	3
Potassium	ppm	ASTM D5185m	>20	4	9	7
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.8	0.6
Nitration	Abs/cm	*ASTM D7624	>20	11.5	12.9	11.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.5	27.0	26.0
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.6	28.2	24.9
Base Number (BN)	mg KOH/g	ASTM D2896	11.0	6.3	4.2	5.6




# **OIL ANALYSIS REPORT**




	_	7
Base Number	-	
12.0 Base	1	
<u>\$</u> 10.0 -		
8.0		
0.10.0 B Base Mumber (ing KOH(g))		
4.0		
2.0		
0.0	4.	*
Nov2/23	Feb 18/2	0,51
~	프	








FLUID PROPI	ERHES	method				history2
Visc @ 100°C	cSt	ASTM D445	11.9	11.3	11.9	12.0

## **GRAPHS**













Certificate 12367

Laboratory Sample No. Lab Number : 06217988 Unique Number : 11096185

: PCA0126904

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 24 Jun 2024 **Tested** : 25 Jun 2024 Diagnosed

: 25 Jun 2024 - Wes Davis

1955 W. North Avenue, Bldg K Melrose Park, IL

US 60160 Contact: Tom Lindeman tlindemann@transervice.com T: (630)376-8946

Transervice - Shop 1920 - Preferred Service

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)