

OIL ANALYSIS REPORT

(43-329HA) 710022

Diesel Engine

DIESEL ENGINE OIL SAE 40 (--- GAL)

Sample Rating Trend



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


| SAMPLE INFORI | MATION | method | limit/base | current | history1 | history2 |
|---|----------|-------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | GFL0121993 | GFL0122037 | GFL0116542 |
| Sample Date | | Client Info | | 25 Jun 2024 | 06 Jun 2024 | 14 May 2024 |
| Machine Age | hrs | Client Info | | 9205 | 9095 | 8902 |
| Oil Age | hrs | Client Info | | 9012 | 193 | 8447 |
| Oil Changed | | Client Info | | Not Changd | Not Changd | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METAL | S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 8 | 7 | 16 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 5 | 2 | 3 |
| Lead | ppm | ASTM D5185m | >40 | 2 | <1 | 3 |
| Copper | ppm | ASTM D5185m | >330 | 1 | 1 | 1 |
| Tin | ppm | ASTM D5185m | >15 | <1 | <1 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 250 | 12 | 19 | 4 |
| Barium | ppm | ASTM D5185m | 10 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 100 | 58 | 58 | 56 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 450 | 957 | 908 | 964 |
| Calcium | ppm | ASTM D5185m | 3000 | 1189 | 1123 | 1198 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 1090 | 904 | 1009 |
| Zinc | ppm | ASTM D5185m | 1350 | 1326 | 1192 | 1265 |
| Sulfur | ppm | ASTM D5185m | 4250 | 3467 | 3032 | 3502 |
| CONTAMINAN | TS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 5 | 5 | 6 |
| Sodium | ppm | ASTM D5185m | >216 | 5 | 1 | 2 |
| Potassium | ppm | ASTM D5185m | >20 | 3 | 2 | 4 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.6 | 0.4 | 0.8 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 9.7 | 7.9 | 12.6 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 20.5 | 19.6 | 23.5 |
| FLUID DEGRADATION method limit/base current history1 history2 | | | | | | |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 18.4 | 16.5 | 24.8 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 8.4 | 8.8 | 6.0 |
| | | | | | | |



OIL ANALYSIS REPORT










| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |


| FLUID PROPI | ERTIES | method | | | | history2 |
|--------------|--------|-----------|------|------|------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 13.2 | 13.6 | 12.6 |

GRAPHS













Certificate 12367

Laboratory Sample No.

Test Package : FLEET

: GFL0121993 Lab Number : 06222177 Unique Number : 11100374

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Jun 2024 **Tested** : 28 Jun 2024 Diagnosed

: 28 Jun 2024 - Wes Davis

GFL Environmental - 652 - Fredericksburg Hauling

10954 Houser Drive Fredericksburg, VA US 22408

Contact: WILLIAM MILO wmilo@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GFL652 [WUSCAR] 06222177 (Generated: 06/29/2024 10:52:28) Rev: 1

Submitted By: TECHNICIAN ACCOUNT

T:

F: