




OIL ANALYSIS REPORT



Area
(24564UA)
 Machine Id
819013
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0121992	GFL0122052	GFL0111879
Sample Date	Client Info		25 Jun 2024	03 Jun 2024	16 Apr 2024
Machine Age	hrs	Client Info	11270	11150	11010
Oil Age	hrs	Client Info	10949	10969	181
Oil Changed	Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	45	29	21
Chromium	ppm	ASTM D5185m >20	<1	<1	1
Nickel	ppm	ASTM D5185m >5	2	0	2
Titanium	ppm	ASTM D5185m >2	<1	<1	<1
Silver	ppm	ASTM D5185m >2	0	0	<1
Aluminum	ppm	ASTM D5185m >20	10	8	5
Lead	ppm	ASTM D5185m >40	13	8	3
Copper	ppm	ASTM D5185m >330	4	2	2
Tin	ppm	ASTM D5185m >15	2	2	2
Vanadium	ppm	ASTM D5185m	<1	0	<1
Cadmium	ppm	ASTM D5185m	0	0	1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 250	14	20	19
Barium	ppm	ASTM D5185m 10	<1	<1	0
Molybdenum	ppm	ASTM D5185m 100	72	67	60
Manganese	ppm	ASTM D5185m	<1	1	1
Magnesium	ppm	ASTM D5185m 450	1152	991	888
Calcium	ppm	ASTM D5185m 3000	1405	1241	1135
Phosphorus	ppm	ASTM D5185m 1150	1345	1179	1088
Zinc	ppm	ASTM D5185m 1350	1622	1355	1212
Sulfur	ppm	ASTM D5185m 4250	3745	3474	3442

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	19	18	13
Sodium	ppm	ASTM D5185m >216	8	4	2
Potassium	ppm	ASTM D5185m >20	9	8	4

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.7	0.4	0.4
Nitration	Abs/cm	*ASTM D7624 >20	11.3	9.5	7.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	26.4	22.9	19.8


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	22.5	18.4	15.1
Base Number (BN)	mg KOH/g	ASTM D2896 8.5	6.9	7.5	8.5




OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	14.7	14.5

GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0121992
 Lab Number : 06222178
 Unique Number : 11100375
 Test Package : FLEET

Received : 27 Jun 2024
 Tested : 28 Jun 2024
 Diagnosed : 29 Jun 2024 - Don Baldrige

GFL Environmental - 652 - Fredericksburg Hauling
 10954 Houser Drive
 Fredericksburg, VA
 US 22408
 Contact: WILLIAM MILO
 wmilo@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: