


OIL ANALYSIS REPORT

Sample Rating Trend



WEAR



Area
(69926Z) Walgreens - Tractor
 Machine Id
[Walgreens - Tractor] 136A624029
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. No other contaminants were detected in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0128191	PCA0123383	---
Sample Date	Client Info			19 Jun 2024	05 Apr 2024	---
Machine Age	mls	Client Info		92890	61895	---
Oil Age	mls	Client Info		30995	61895	---
Oil Changed	Client Info			Not Chngd	Changed	---
Sample Status				ABNORMAL	ABNORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	<1.0	---
Water	WC Method	>0.2		NEG	NEG	---
Glycol	WC Method			NEG	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	39	83	---
Chromium	ppm	ASTM D5185m	>5	4	9	---
Nickel	ppm	ASTM D5185m	>2	2	2	---
Titanium	ppm	ASTM D5185m		0	<1	---
Silver	ppm	ASTM D5185m	>3	<1	<1	---
Aluminum	ppm	ASTM D5185m	>30	32	84	---
Lead	ppm	ASTM D5185m	>30	0	<1	---
Copper	ppm	ASTM D5185m	>150	▲ 165	▲ 248	---
Tin	ppm	ASTM D5185m	>5	2	7	---
Vanadium	ppm	ASTM D5185m		<1	<1	---
Cadmium	ppm	ASTM D5185m		0	<1	---






ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	8	28	---
Barium	ppm	ASTM D5185m	0	0	2	---
Molybdenum	ppm	ASTM D5185m	50	61	45	---
Manganese	ppm	ASTM D5185m	0	3	7	---
Magnesium	ppm	ASTM D5185m	950	951	542	---
Calcium	ppm	ASTM D5185m	1050	1340	1832	---
Phosphorus	ppm	ASTM D5185m	995	975	775	---
Zinc	ppm	ASTM D5185m	1180	1260	918	---
Sulfur	ppm	ASTM D5185m	2600	2631	2077	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	7	11	---
Sodium	ppm	ASTM D5185m		4	6	---
Potassium	ppm	ASTM D5185m	>20	81	211	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.8	---
Nitration	Abs/cm	*ASTM D7624	>20	9.0	11.9	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	24.2	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.4	27.5	---
Base Number (BN)	mg KOH/g	ASTM D2896		7.4	5.8	---





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.1	10.0

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0128191 **Received** : 27 Jun 2024
Lab Number : 06223015 **Tested** : 28 Jun 2024
Unique Number : 11101212 **Diagnosed** : 28 Jun 2024 - Jonathan Hester
Test Package : FLEET

Transervice - Shop 1373 - Berkeley-Anderson/Pendergrass
 101 Alliance Parkway
 Willamston, SC
 US 29697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact: Sonny Boucher
 sboucher@transervice.com
 T: (864)226-2304
 F: (864)226-2329