OIL ANALYSIS REPORT

OIL DIAGNOSTICS

Sample Rating Trend



NORMAL

Machine Id
DT638
Component
Front Differential
Fluid
CHEVRON RPM SYNTHETIC GEAR 75W90 (4 mls)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0120542**	PCA0080468	PCA0050635
Sample Date		Client Info		**24 Jun 2024**	19 Dec 2022	19 Aug 2021
Machine Age	mls	Client Info		**246874**	200163	0
Oil Age	mls	Client Info		**129838**	28273	0
Oil Changed		Client Info		**Changed**	Not Changd	Changed
Sample Status				**NORMAL**	ABNORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>.2	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	**202**	103	126
Chromium	ppm	ASTM D5185m	>8	**2**	<1	1
Nickel	ppm	ASTM D5185m	>20	**6**	3	4
Titanium	ppm	ASTM D5185m	>4	**<1**	<1	<1
Silver	ppm	ASTM D5185m		**0**	0	0
Aluminum	ppm	ASTM D5185m	>30	**23**	12	6
Lead	ppm	ASTM D5185m	>25	**0**	0	0
Copper	ppm	ASTM D5185m	>50	**<1**	<1	<1
Tin	ppm	ASTM D5185m	>5	**0**	0	0
Antimony	ppm	ASTM D5185m	>5	**---**	---	0
Vanadium	ppm	ASTM D5185m		**<1**	0	<1
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**196**	226	228
Barium	ppm	ASTM D5185m		**<1**	0	0
Molybdenum	ppm	ASTM D5185m		**15**	16	0
Manganese	ppm	ASTM D5185m		**2**	1	1
Magnesium	ppm	ASTM D5185m		**124**	122	4
Calcium	ppm	ASTM D5185m		**232**	231	16
Phosphorus	ppm	ASTM D5185m		**1291**	1240	1415
Zinc	ppm	ASTM D5185m		**211**	194	13
Sulfur	ppm	ASTM D5185m		**23089**	25056	23580

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>230	**38**	30	29
Sodium	ppm	ASTM D5185m		**3**	2	1
Potassium	ppm	ASTM D5185m	>20	**2**	<1	0

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	▲ MODER	LIGHT
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

OIL ANALYSIS REPORT

Viscosity @ 40°C



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	110	**81.3**	84.7	97.0

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				*no image*	*no image*
Bottom				*no image*	*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0120542
Lab Number : 06223868
Unique Number : 11102065
Test Package : FLEET

Received : 28 Jun 2024
Tested : 29 Jun 2024
Diagnosed : 30 Jun 2024 - Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

NW WHITE & CO - GREER DIVISION
1060 ROGERS BRIDGE RD
DUNCAN, SC
US 29334
Contact: Matt Quinlan
mquinlan@nwwhite.com
T: (864)905-8506
F:

Report Id: NWWDUN [WUSCAR] 06223868 (Generated: 06/30/2024 11:25:48) Rev: 1

Submitted By: moved here from NWWGRE - Matt Quinlan