




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
426145-4623

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0125247	GFL0103969	GFL0100484
Sample Date	Client Info		20 Jun 2024	07 Feb 2024	16 Nov 2023
Machine Age	hrs	Client Info	18970	18633	18320
Oil Age	hrs	Client Info	0	0	18320
Oil Changed	Client Info		Not Changed	Changed	Not Changed
Sample Status			NORMAL	ABNORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	▲ 3.8	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	8	67	17
Chromium	ppm	ASTM D5185m >20	<1	1	<1
Nickel	ppm	ASTM D5185m >4	<1	0	0
Titanium	ppm	ASTM D5185m	<1	0	<1
Silver	ppm	ASTM D5185m >3	<1	0	0
Aluminum	ppm	ASTM D5185m >20	3	● 8	6
Lead	ppm	ASTM D5185m >40	<1	<1	<1
Copper	ppm	ASTM D5185m >330	76	111	32
Tin	ppm	ASTM D5185m >15	<1	<1	<1
Vanadium	ppm	ASTM D5185m	<1	0	<1
Cadmium	ppm	ASTM D5185m	<1	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	6	234	397
Barium	ppm	ASTM D5185m 0	<1	19	2
Molybdenum	ppm	ASTM D5185m 60	59	127	128
Manganese	ppm	ASTM D5185m 0	<1	9	5
Magnesium	ppm	ASTM D5185m 1010	951	660	723
Calcium	ppm	ASTM D5185m 1070	1080	1550	1555
Phosphorus	ppm	ASTM D5185m 1150	1132	677	738
Zinc	ppm	ASTM D5185m 1270	1235	850	901
Sulfur	ppm	ASTM D5185m 2060	3181	2333	2716

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	5	▲ 25	19
Sodium	ppm	ASTM D5185m	2	13	11
Potassium	ppm	ASTM D5185m >20	2	22	18

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.1	0.8	0.1
Nitration	Abs/cm	*ASTM D7624 >20	5.3	11.3	5.0
Sulfation	Abs/.1mm	*ASTM D7415 >30	17.9	24.9	22.8

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	13.6	20.4	15.9
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	9.3	7.8	10.1







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	▲ 12.3	13.5

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0125247 **Received** : 28 Jun 2024
Lab Number : **06224232** **Tested** : 01 Jul 2024
Unique Number : 11102429 **Diagnosed** : 01 Jul 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 865 - East Mount Hauling
 7213 East Mount Houston Road
 Houston, TX
 US 77050
 Contact: Saul Castillo
 saul.castillo@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)