


OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id SJB700 Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| QTS) Mwydd22 Jwdd23 Mwdd23 Jwdd23 Augld23 Swdd23 Novd203 Fedd24 Jwdd24 | | | | | | |
|--|-------------|----------------------------|--------------|--------------|--------------|--------------|
| SAMPLE INFOR | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0120991 | PCA0116893 | PCA0105802 |
| Sample Date | | Client Info | | 14 Jun 2024 | 28 Feb 2024 | 08 Nov 2023 |
| Machine Age | mls | Client Info | | 143851 | 0 | 131263 |
| Oil Age | mls | Client Info | | 4027 | 0 | 9462 |
| Oil Changed | | Client Info | | Changed | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METAL | .S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 17 | 21 | 14 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | 1 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Silver | ppm | ASTM D5185m | >3 | <1 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 4 | 3 | 2 |
| Lead | ppm | ASTM D5185m | >40 | 2 | 2 | 0 |
| Copper | ppm | ASTM D5185m | | 2 | 2 | 0 |
| Tin | ppm | ASTM D5185m | >15 | <1 | 1 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 2 | 4 | 5 | 1 |
| Barium | ppm | ASTM D5185m | | <1 | 2 | 4 |
| Molybdenum | ppm | ASTM D5185m | 50 | 67 | 66 | 67 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | 950 | 953 | 884 | 888 |
| Calcium | ppm | ASTM D5185m | 1050 | 1142 | 1196 | 1220 |
| Phosphorus | ppm | ASTM D5185m | 995 | 1061 | 1022 | 1058 |
| Zinc Sulfur | ppm | ASTM D5185m ASTM D5185m | 1180 2600 | 1274 2936 | 1196 3153 | 1244 3496 |
| CONTAMINAN | | | limit/base | | | |
| | | method | | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 4 | 4 | 0 |
| Sodium Potassium | ppm ppm | ASTM D5185m ASTM D5185m | >20 | <1 2 | 3 | 0 |
| | ррпп | | | | | |
| INFRA-RED | 0/ | method *ASTM D7844 | limit/base | current | history1 | history2 |
| Soot % Nitration | % Abs/cm | *ASTM D7844 | >3 >20 | 0.8 8.4 | 1.1 9.4 | 1.5 9.6 |
| Sulfation | Abs/.1mm | *ASTM D7624 | | 8.4 19.5 | 19.7 | 20.7 |
| | | | | | | |
| FLUID DEGRAI | | | limit/base | | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 15.1 | 15.1 | 15.7 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | | 9.4 | 9.2 | 9.8 |



OIL ANALYSIS REPORT







Certificate 12367

Laboratory Sample No.

: PCA0120991 Lab Number : 06225970 Unique Number : 11109463

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 02 Jul 2024 **Tested** : 03 Jul 2024

Diagnosed : 03 Jul 2024 - Wes Davis Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MILLER TRUCK LEASING #114

63 REPAUPO STATION ROAD LOGAN TOWNSHIP, NJ

US 08085 Contact: ED DAVIS edavis@millertransgroup.com

T: (856)214-3521 F: (856)214-3663

Contact/Location: ED DAVIS - MILLOG