

OIL ANALYSIS REPORT

Sample Rating Trend



VISCOSITY



Machine Id

CE0435

Component

Diesel Engine

Fluid

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0120996	---	---
Sample Date	Client Info		10 Jun 2024	---	---
Machine Age	mls	Client Info	159096	---	---
Oil Age	mls	Client Info	0	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			ATTENTION	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	7	---
Chromium	ppm	ASTM D5185m	>20	<1	---
Nickel	ppm	ASTM D5185m	>4	<1	---
Titanium	ppm	ASTM D5185m		<1	---
Silver	ppm	ASTM D5185m	>3	<1	---
Aluminum	ppm	ASTM D5185m	>20	3	---
Lead	ppm	ASTM D5185m	>40	0	---
Copper	ppm	ASTM D5185m	>330	4	---
Tin	ppm	ASTM D5185m	>15	<1	---
Vanadium	ppm	ASTM D5185m		<1	---
Cadmium	ppm	ASTM D5185m		<1	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	112	---
Barium	ppm	ASTM D5185m	0	<1	---
Molybdenum	ppm	ASTM D5185m	50	71	---
Manganese	ppm	ASTM D5185m	0	<1	---
Magnesium	ppm	ASTM D5185m	950	461	---
Calcium	ppm	ASTM D5185m	1050	877	---
Phosphorus	ppm	ASTM D5185m	995	548	---
Zinc	ppm	ASTM D5185m	1180	627	---
Sulfur	ppm	ASTM D5185m	2600	2030	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	---
Sodium	ppm	ASTM D5185m		2	---
Potassium	ppm	ASTM D5185m	>20	4	---
Fuel	%	ASTM D3524	>5	1.5	---






INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0	---
Nitration	Abs/cm	*ASTM D7624	>20	6.9	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.5	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.3	---
Base Number (BN)	mg KOH/g	ASTM D2896		5.0	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	● 7.96	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0120996 **Received** : 02 Jul 2024
Lab Number : 06225986 **Tested** : 08 Jul 2024
Unique Number : 11109479 **Diagnosed** : 09 Jul 2024 - Jonathan Hester
Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN)

MILLER TRUCK LEASING #114
 63 REPAUPO STATION ROAD
 LOGAN TOWNSHIP, NJ
 US 08085
 Contact: ED DAVIS
 edavis@millertransgroup.com
 T: (856)214-3521
 F: (856)214-3663

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)