

PROBLEM SUMMARY

Area (29KM2B) 923034-260317

Diesel Engine Fluid PETRO CANADA DURON SHP 15W40 (--- GAL)

COMPONENT CONDITION SUMMARY





RECOMMENDATION

We advise that you check the fuel injection system. We recommend that you drain the oil and perform a filter service on this component if not already done. We recommend an early resample to monitor this condition.

PROBLEMATIC TEST RESULTS								
Sample Status				SEVERE	NORMAL	NORMAL		
Fuel	%	ASTM D3524	>3.0	1 3.0	<1.0	<1.0		
Visc @ 100°C	cSt	ASTM D445	15.4	12.3	13.6	14.3		

Customer Id: GFL837 Sample No.: GFL0124136 Lab Number: 06228310 Test Package: FLEET



To manage this report scan the QR code

To discuss the diagnosis or test data: Don Baldridge +1 don.b505@comcast.net

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com



RECOMMENDED ACTIONS							
Action	Status	Date	Done By	Description			
Change Fluid			?	We recommend that you drain the oil and perform a filter service on this component if not already done.			
Change Filter			?	We recommend that you drain the oil and perform a filter service on this component if not already done.			
Resample			?	We recommend an early resample to monitor this condition.			
Check Fuel/injector System			?	We advise that you check the fuel injection system.			

HISTORICAL DIAGNOSIS

13 May 2024 Diag: Wes Davis

Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.





24 Apr 2024 Diag: Don Baldridge

Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.





NORMAL

29 Mar 2024 Diag: Don Baldridge Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT

Area (29KM2B) 923034-260317

Diesel Engine Fluid PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

We advise that you check the fuel injection system. We recommend that you drain the oil and perform a filter service on this component if not already done. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

Contamination

There is a high amount of fuel present in the oil.

Fluid Condition

Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.



SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0124136	GFL0117229	GFL0117162
Sample Date		Client Info		01 Jul 2024	13 May 2024	24 Apr 2024
Machine Age	hrs	Client Info		21749	21956	21511
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				SEVERE	NORMAL	NORMAL
CONTAMINAT		method	limit/base	current	history1	history2
			0.0		NEO	NEO
Water		WC Method	>0.2	NEG	NEG	NEG
GIYCOI		WC Method		NEG	NEG	NEG
WEAR METAL	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>75	56	25	12
Chromium	ppm	ASTM D5185m	>5	3	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>15	3	4	2
Lead	ppm	ASTM D5185m	>25	8	1	<1
Copper	ppm	ASTM D5185m	>100	2	1	<1
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
ADDITIVES Boron	mag	method ASTM D5185m	limit/base	current 5	history1 4	history2 16
ADDITIVES Boron Barium	ppm ppm	method ASTM D5185m ASTM D5185m	limit/base 0 0	current 5 0	history1 4 <1	history2 16 0
ADDITIVES Boron Barium Molybdenum	ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60	current 5 0 57	history1 4 <1 64	history2 16 0 55
ADDITIVES Boron Barium Molybdenum Manganese	ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0	current 5 0 57 <1	history1 4 <1 64 <1	history2 16 0 55 <1
ADDITIVES Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010	current 5 0 57 <1 942	history1 4 <1 64 <1 986	history2 16 0 55 <1 596
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070	current 5 0 57 <1 942 1117	history1 4 <1 64 <1 986 1105	history2 16 0 55 <1 596 1761
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150	current 5 0 57 <1 942 1117 1024	history1 4 <1 64 <1 986 1105 1126	history2 16 0 55 <1 596 1761 856
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270	current 5 0 57 <1 942 1117 1024 1255	history1 4 <1 64 <1 986 1105 1126 1307	history2 16 0 55 <1 596 1761 856 1059
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060	current 5 0 57 <1 942 1117 1024 1255 3053	history1 4 <1 64 <1 986 1105 1126 1307 3585	history2 16 0 55 <1 596 1761 856 1059 3099
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base	current 5 0 57 <1 942 1117 1024 1255 3053 current	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1	history2 16 0 55 <1 596 1761 856 1059 3099 history2
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon	ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25	current 5 0 57 <1 942 1117 1024 1255 3053 current 7	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium	ppm ppm ppm ppm ppm ppm ppm ppm ppm TS	method ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 ⊳20	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel	ppm ppm ppm ppm ppm ppm ppm ppm ppm TS	method ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 >20 >20 >3.0	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 >20 >3.0	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED	ppm ppm ppm ppm ppm ppm ppm ppm TS ppm ppm ppm	method ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 >20 >3.0 limit/base	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED Soot %	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D3524 method *ASTM D3524	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 >20 >3.0 limit/base >6	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0 current 1.8	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1 1.2	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2 0.1
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 limit/base >25 >20 >3.0 limit/base >6 >20	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0 current 1.8 15.7	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1 1.2 9.8	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2 0.1 9.8
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m	limit/base 0 0 0 1010 1070 1150 1270 2060 2060 2060 2060 225 20 >20 >3.0 20 20 20 20 20 20 20 20 20 20 20 20 20	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0 current 1.8 15.7 29.2	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1 1.2 9.8 21.8	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2 0.1 9.8 19.4
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m	limit/base 0 0 60 0 1010 1070 1150 1270 2060 2060 225 20 >20 >20 >3.0 limit/base >6 >20 >20 >3.0	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0 current 1.8 15.7 29.2	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1 1.2 9.8 21.8 history1	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2 0.1 9.8 19.4
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium Fuel INFRA-RED Soot % Nitration Sulfation FLUID DEGRAE Oxidation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m *ASTM D7844 *ASTM D7415	limit/base 0 0 0 0 1010 1070 1150 1270 2060 2060 2060 225 20 >3.0 1imit/base >6 >20 >30 20 20 3.0 20 20 20 20 20 20 20 20 20 20 20 20 20	current 5 0 57 <1 942 1117 1024 1255 3053 current 7 6 2 13.0 current 1.8 15.7 29.2 current	history1 4 <1 64 <1 986 1105 1126 1307 3585 history1 4 18 2 <1.0 history1 1.2 9.8 21.8 history1 16.4	history2 16 0 55 <1 596 1761 856 1059 3099 history2 4 6 0 <1.0 history2 0.1 9.8 19.4 history2 16.3



OIL ANALYSIS REPORT









VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	12.3	13.6	14.3
GRAPHS						







Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 GFL Environmental - 837 - Harrison TS Sample No. : GFL0124136 Received : 05 Jul 2024 22820 S State Route 291 Lab Number : 06228310 Tested : 09 Jul 2024 Harrisonville, MO Unique Number : 11111803 Diagnosed : 09 Jul 2024 - Don Baldridge US 64701 Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel) Contact: SARA PATRICK Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. spatrick@gflenv.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Report Id: GFL837 [WUSCAR] 06228310 (Generated: 07/09/2024 10:26:31) Rev: 1

Submitted By: JEREMY BROWN

Page 4 of 4