




OIL ANALYSIS REPORT



Area
(24553UA)
 Machine Id
811008
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

| | method | limit/base | current | history1 | history2 |
|---------------|-------------|-------------|--------------------|-------------|-------------|
| Sample Number | Client Info | | GFL0127180 | GFL0116551 | GFL0122044 |
| Sample Date | Client Info | | 04 Jul 2024 | 10 Jun 2024 | 17 May 2024 |
| Machine Age | hrs | Client Info | 9052 | 8866 | 8718 |
| Oil Age | hrs | Client Info | 8736 | 8698 | 168 |
| Oil Changed | Client Info | | Changed | Not Changd | Not Changd |
| Sample Status | | | NORMAL | NORMAL | NORMAL |

CONTAMINATION

| | method | limit/base | current | history1 | history2 |
|--------|-----------|------------|----------------|----------|----------|
| Fuel | WC Method | >3.0 | <1.0 | <1.0 | <1.0 |
| Water | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | WC Method | | NEG | NEG | NEG |

WEAR METALS

| | method | limit/base | current | history1 | history2 |
|----------|--------|------------------|--------------|----------|----------|
| Iron | ppm | ASTM D5185m >120 | 8 | 6 | 3 |
| Chromium | ppm | ASTM D5185m >20 | 1 | <1 | 0 |
| Nickel | ppm | ASTM D5185m >5 | 3 | <1 | <1 |
| Titanium | ppm | ASTM D5185m >2 | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m >2 | <1 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m >20 | 5 | 2 | <1 |
| Lead | ppm | ASTM D5185m >40 | <1 | <1 | <1 |
| Copper | ppm | ASTM D5185m >330 | 2 | 1 | 0 |
| Tin | ppm | ASTM D5185m >15 | <1 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | <1 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | <1 | 0 | 0 |

ADDITIVES

| | method | limit/base | current | history1 | history2 |
|------------|--------|------------------|--------------|----------|----------|
| Boron | ppm | ASTM D5185m 0 | 17 | 19 | 27 |
| Barium | ppm | ASTM D5185m 0 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m 60 | 71 | 60 | 59 |
| Manganese | ppm | ASTM D5185m 0 | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m 1010 | 1126 | 964 | 955 |
| Calcium | ppm | ASTM D5185m 1070 | 1346 | 1278 | 1173 |
| Phosphorus | ppm | ASTM D5185m 1150 | 1233 | 1058 | 1058 |
| Zinc | ppm | ASTM D5185m 1270 | 1546 | 1332 | 1280 |
| Sulfur | ppm | ASTM D5185m 2060 | 3770 | 3866 | 3823 |

CONTAMINANTS

| | method | limit/base | current | history1 | history2 |
|-----------|--------|-----------------|----------|----------|----------|
| Silicon | ppm | ASTM D5185m >25 | 6 | 3 | 4 |
| Sodium | ppm | ASTM D5185m | 3 | <1 | 0 |
| Potassium | ppm | ASTM D5185m >20 | 7 | 4 | 0 |

INFRA-RED




| | method | limit/base | current | history1 | history2 |
|-----------|----------|-----------------|-------------|----------|----------|
| Soot % | % | *ASTM D7844 >4 | 0.5 | 0.4 | 0.3 |
| Nitration | Abs/cm | *ASTM D7624 >20 | 8.0 | 6.6 | 5.6 |
| Sulfation | Abs/.1mm | *ASTM D7415 >30 | 19.0 | 18.8 | 17.9 |

FLUID DEGRADATION

| | method | limit/base | current | history1 | history2 |
|------------------|----------|-----------------|-------------|----------|----------|
| Oxidation | Abs/.1mm | *ASTM D7414 >25 | 14.6 | 13.8 | 13.2 |
| Base Number (BN) | mg KOH/g | ASTM D2896 9.8 | 8.0 | 8.4 | 8.4 |







OIL ANALYSIS REPORT



| VISUAL | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 | |
|------------------|--------|------------|---------|-------------|----------|------|
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | 13.9 | 14.0 | 14.3 |

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0127180 **Received** : 08 Jul 2024
Lab Number : **06229890** **Tested** : 09 Jul 2024
Unique Number : 11113383 **Diagnosed** : 09 Jul 2024 - Don Baldrige
Test Package : FLEET

GFL Environmental - 652 - Fredericksburg Hauling
 10954 Houser Drive
 Fredericksburg, VA
 US 22408
 Contact: WILLIAM MILO
 wmilo@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)