

OIL ANALYSIS REPORT

Area (65235Z) Walgreens - Tractor [Walgreens - Tractor] 136A6

Diesel Engine Fluic

PETRO CANADA DURON SHP 10W30 (11 G

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


624211						
GAL)			Mar2024	Jul2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0120785	PCA0106554	
Sample Date		Client Info		01 Jul 2024	12 Mar 2024	
Machine Age	mls	Client Info		117654	78900	
Oil Age	mls	Client Info		30000	50000	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	ABNORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	37	A 91	
Chromium	ppm	ASTM D5185m	>5	2	5	
Nickel	ppm	ASTM D5185m	>2	0	1	
Titanium	ppm	ASTM D5185m		0	<1	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>30	36	149	
Lead	ppm	ASTM D5185m	>30	0	2	
Copper	ppm	ASTM D5185m	>150	38	<u> </u>	
Tin	ppm	ASTM D5185m	>5	2	6	
Vanadium	ppm	ASTM D5185m		0	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	8	18	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	56	49	
Manganese	ppm	ASTM D5185m	0	1	4	
Magnesium	ppm	ASTM D5185m	950	769	546	
Calcium	ppm	ASTM D5185m	1050	1264	1681	
Phosphorus	ppm	ASTM D5185m	995	888	755	
Zinc	ppm	ASTM D5185m	1180	1091	893	
Sulfur	ppm	ASTM D5185m	2600	2557	2069	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5	8	
Sodium	ppm	ASTM D5185m		4	9	
Potassium	ppm	ASTM D5185m	>20	80	348	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.8	
Nitration	Abs/cm	*ASTM D7624	>20	10.0	12.4	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	24.5	
FLUID DEGRA	DAT <u>ION</u>	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.6	28.1	
Base Number (BN)	mg KOH/g	ASTM D7414 ASTM D2896	~	6.1	4.8	
Dase Number (DN)	ing NOTI/g	AO HWI D2030		0.1	т.0	


Sample Rating Trend

NORMAL





OIL ANALYSIS REPORT





		and a file of a	l'and to the second		In the transmission	history O
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.8	10.6	
0 - iron 0 - nickel 0 - 0 - 0 - 0 - 0 - 0 - 0 - 0 - 0 - 0 -	<u> </u>					
Mar12/24			Jul1/24			





50

Contact/Location: Robert Beal - TSV1369