


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL


Area
(65352Z) Walgreens - Tractor
 Machine Id
[Walgreens - Tractor] 136A624153
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS
Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. No other contaminants were detected in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0127116	PCA0119383	---
Sample Date	Client Info		03 Jun 2024	10 Apr 2024	---
Machine Age	mls	Client Info	165097	136608	---
Oil Age	mls	Client Info	28489	50000	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	ABNORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	---
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >80	36	▲ 112	---
Chromium	ppm	ASTM D5185m >5	1	▲ 7	---
Nickel	ppm	ASTM D5185m >2	0	1	---
Titanium	ppm	ASTM D5185m	0	<1	---
Silver	ppm	ASTM D5185m >3	0	0	---
Aluminum	ppm	ASTM D5185m >30	25	112	---
Lead	ppm	ASTM D5185m >30	0	<1	---
Copper	ppm	ASTM D5185m >150	76	▲ 156	---
Tin	ppm	ASTM D5185m >5	0	4	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	5	13	---
Barium	ppm	ASTM D5185m 0	0	<1	---
Molybdenum	ppm	ASTM D5185m 50	59	51	---
Manganese	ppm	ASTM D5185m 0	0	5	---
Magnesium	ppm	ASTM D5185m 950	881	648	---
Calcium	ppm	ASTM D5185m 1050	1217	1673	---
Phosphorus	ppm	ASTM D5185m 995	1009	896	---
Zinc	ppm	ASTM D5185m 1180	1268	1058	---
Sulfur	ppm	ASTM D5185m 2600	2703	2156	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	3	11	---
Sodium	ppm	ASTM D5185m	2	5	---
Potassium	ppm	ASTM D5185m >20	58	263	---






INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.7	1.6	---
Nitration	Abs/cm	*ASTM D7624 >20	9.6	17.2	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	21.0	28.0	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.2	34.4	---
Base Number (BN)	mg KOH/g	ASTM D2896	7.7	3.1	---





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.4	11.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0127116
Lab Number : 06235404
Unique Number : 11124238
Test Package : FLEET

Received : 15 Jul 2024
Tested : 15 Jul 2024
Diagnosed : 15 Jul 2024 - Don Baldrige

Transervice - Shop 1370 - Berkeley-Perrysburg
 28727 Oregon Road
 Perrysburg, OH
 US 43551
 Contact: Curtis Hart
 chart@transervice.com
 T: (419)666-3277
 F: (419)666-3279

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)