


OIL ANALYSIS REPORT



NORMAL



DT39 Component Transmission (Auto) **DEXRON III (--- GAL)**

DIAGNOSIS

Machine Id

Recommendation

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DEXRON III. Please confirm.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

| | | Janzuz | 2 38112023 | 002023 31 | 12024 | |
|------------------|---------|-------------|------------|-------------|----------------------|--------------------------|
| SAMPLE INFOR | RMATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0116163 | PCA0107498 | PCA0084976 |
| Sample Date | | Client Info | | 11 Jul 2024 | 11 Oct 2023 | 16 Jan 2023 |
| Machine Age | mls | Client Info | | 151896 | 112618 | 26194 |
| Oil Age | mls | Client Info | | 75000 | 75000 | 26194 |
| Oil Changed | | Client Info | | Changed | Not Changd | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ΓΙΟΝ | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.1 | NEG | NEG | NEG |
| WEAR METAI | _S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >160 | 64 | 62 | 105 |
| Chromium | ppm | ASTM D5185m | >5 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >5 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >5 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >50 | 33 | 24 | 50 |
| Lead | ppm | ASTM D5185m | >50 | 18 | 27 | 42 |
| Copper | ppm | ASTM D5185m | >225 | 30 | 107 | 22 |
| Tin | ppm | ASTM D5185m | >10 | 5 | 1 | 8 |
| Antimony | ppm | ASTM D5185m | | | | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 71 | 104 | 97 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 1 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | 2 |
| Magnesium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Calcium | ppm | ASTM D5185m | | 77 | 109 | 58 |
| Phosphorus | ppm | ASTM D5185m | | 205 | 265 | 258 |
| Zinc | ppm | ASTM D5185m | | 0 | 45 | 5 |
| Sulfur | ppm | ASTM D5185m | | 1535 | 1701 | 1093 |
| CONTAMINAN | NTS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >20 | 5 | 7 | 6 |
| Sodium | ppm | ASTM D5185m | | 6 | 5 | 4 |
| Potassium | ppm | ASTM D5185m | >20 | 2 | <1 | 6 |
| VISUAL | | method | limit/base | current | history1 | history2 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | LIGHT | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.1 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | Ş <u>⊨</u> Emitted I | By: Ra <u>н</u> bRiddick |
| | | | | | | Page 1 of 2 |





OIL ANALYSIS REPORT





Ferrous Alloys 110 100 90 80 70 30 20 0ct11/23







Certificate 12367

Laboratory Sample No.

: PCA0116163 Lab Number : 06236643 Unique Number : 11125477 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024

Tested : 16 Jul 2024 Diagnosed

: 16 Jul 2024 - Wes Davis

NW WHITE & CO - COLUMBIA DIVISION 100 INDEPENDENCE BLVD

COLUMBIA, SC US 29210

Contact: GEORGE EDWARDS gedwards@nwwhite.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWCOL [WUSCAR] 06236643 (Generated: 07/16/2024 13:38:09) Rev: 1

Submitted By: Paul Riddick

T:

F: