

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **426147** Component **Transmission (Auto)** Fluid **{not provided} (--- GAL)**

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Transmission)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		GFL0128732	GFL0112043	GFL0094088			
Sample Date		Client Info		10 Jul 2024	10 May 2024	10 Nov 2023			
Machine Age	mls	Client Info		352281	342476	317495			
Oil Age	mls	Client Info		352281	342476	317495			
Oil Changed		Client Info		Not Changd	Changed	Changed			
Sample Status				NORMAL	NORMAL	NORMAL			
CONTAMINATI	ON	method	limit/base	current	history1	history2			
Water		WC Method		NEG	NEG	NEG			
WEAR METALS	6	method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>160	20	27	46			
Chromium	ppm	ASTM D5185m	>5	0	0	<1			
Nickel	ppm	ASTM D5185m		0	0	0			
Titanium	ppm	ASTM D5185m		0	0	<1			
Silver	ppm	ASTM D5185m	>5	0	0	0			
Aluminum	ppm	ASTM D5185m		3	5	8			
Lead	ppm	ASTM D5185m		5 <1	1	3			
Copper	ppm	ASTM D5185m		146	60	49			
Tin	ppm	ASTM D5185m		0	0	<1			
Vanadium	ppm	ASTM D5185m	>10	0	0	0			
Cadmium	ppm	ASTM D5185m		0	0	0			
ADDITIVES	1-1-	method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		44	23	47			
Barium	ppm	ASTM D5185m		0	0	<1			
Molybdenum	ppm	ASTM D5185m		0	0	<1			
Manganese	ppm	ASTM D5185m		<1	<1	0			
Magnesium	ppm	ASTM D5185m		2	1	2			
Calcium	ppm	ASTM D5185m		455	337	208			
Phosphorus	ppm	ASTM D5185m		471	431	342			
Zinc	ppm	ASTM D5185m		24	29	24			
Sulfur	ppm	ASTM D5185m		1415	1088	1003			
			limit/bass						
CONTAMINAN		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>20	5	6	6			
Sodium	ppm	ASTM D5185m		7	3	0			
Potassium	ppm	ASTM D5185m	>20	<1	<1	3			
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE	NONE	NONE			
Debris	scalar	*Visual	NONE	NONE	NONE	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML	NORML	NORML			
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG			
Free Water	scalar	*Visual		NEG	NEG	NEG			
2:19:01) Rev: 1				Submitted By: TECHNICIAN ACCOUNT					



OIL ANALYSIS REPORT



	FLUID PROPER	RTIES	method				history2
	Visc @ 40°C	cSt	ASTM D445	5	23.3	25.7	25.66
	SAMPLE IMAG	ES	method	limit/base	e current	history1	history2
24	Color				no image	no image	no image
May10/24	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys		24	24 / Patient PatientPatient Patient Patient Patient Patient Patient Patient Patient Pa			
	May31/23 Nov10/23		May10/24	Jul10/24			
Laboratory Sample No. Lab Number Unique Number Test Package	: 11127098	Recei Teste Diagn	ved :1 d :1 nosed :1	6 Jul 2024 7 Jul 2024 8 Jul 2024 - 5	Sean Felton	ntact: TECHNIC	st Belfort Stre Sugar Land, US 774



Report Id: GFL983 [WUSCAR] 06238264 (Generated: 07/18/2024 12:19:01) Rev: 1

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: Submitted By: TECHNICIAN ACCOUNT Page 2 of 2

T: