

## **CONSTRUCTION EQUIPMENT**

JOHNSONGHERBERT VOLVO A30G 742128 - FRONT LEFT FINAL DR

**Sample No:** PP387383 **Oil Type:** VOLVO

Job No: JOHNSON&HERBERT

VOLVO SAMPLE	E INFORMATIO	N		
Sample Number		PP387383	 	
Sample Date		06 Jun 2019	 	
Machine Hours		1002	 	
Oil Hours		1002	 	
Oil Changed		Changed	 	
Sample Status		NORMAL	 	
VOLVO				
OIL CON	DITION			
Visc @ 40°C	cSt	122	 	
VOLVO	######################################		 	
CONTAN	MOITAMIN			
Silicon	ppm	<b>2</b>	 	
Sodium	ppm	<b>-&lt;1</b>	 	
Potassium	ppm	<b>0</b>	 	
WEAR N	METALS			
Iron	ppm	■101	 	
Copper	ppm	■1	 	
Lead	ppm	<b>0</b>	 	
Tin	ppm	<b>■</b> 0	 	
Aluminum	ppm	<b>0</b>	 	
Chromium	ppm	<b>2</b>	 	
Molybdenum	ppm	1	 	
Nickel	ppm	<b>-&lt;1</b>	 	
Titanium	ppm	0	 	
Silver	ppm	0	 	
Manganese	ppm	2	 	
Vanadium	ppm	0	 	
ADDITIV	VES			
Calcium	ppm	5	 	
Magnesium	ppm	<1	 	
Zinc	ppm	7	 	
Phosphorus	ppm	1104	 	
Barium	ppm	0	 	
Boron	ppm	218	 	
231011	PPIII			



#### STRONGCO EQUIPMENT-EDMONTON

25616 117 Ave NW Acheson, AB CA T7X 6C2 Contact: Jonathan Morton jmorton@strongco.com T: (780)464-1909 F: (780)464-0434

### Diagnosis

Resample at the next service interval to monitor. The fluid was specified as VOLVO, however, a fluid match indicates that this fluid is SAE 80W90 Gear Oil. Please confirm the oil type and grade on your next sample. Please specify the brand, type, and viscosity of the oil on your next sample. All component wear rates are normal. There is no indication of any contamination in the oil. Viscosity of sample indicates oil is within SAE 80W90 range, advise investigate. The condition of the oil is acceptable for the time in service.

Depot:VOLVO3908Unique No:4889122Signed:Kevin MarsonReport Date:27 Jun 2019



# **CONSTRUCTION EQUIPMENT**





