



# CONSTRUCTION EQUIPMENT

## NO UNIT VCP297914 - TRANSMISSION



**Sample No:** VCP297614

**Oil Type:** NOT GIVEN

**Job No:**



### SAMPLE INFORMATION

Sample Number	VCP297614	---	---	---
Sample Date	28 Jul 2022	---	---	---
Machine Hours	0	---	---	---
Oil Hours	0	---	---	---
Oil Changed	N/A	---	---	---
Sample Status	NORMAL	---	---	---

### Strongco Equipment

5179 Fountain St N.  
Breslau, ON  
CA N0B 1M0  
Contact: Villamor Pingol  
vpingol@strongco.com  
T: (519)744-3518  
F: (519)744-3284



### OIL CONDITION

Visc @ 40°C	cSt	32.8	---	---	---
-------------	-----	------	-----	-----	-----



### CONTAMINATION

Silicon	ppm	4	---	---	---
Sodium	ppm	2	---	---	---
Potassium	ppm	<1	---	---	---

### Diagnosis

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample. All component wear rates are normal. There is no indication of any contamination in the fluid. The condition of the fluid is acceptable for the time in service.



### WEAR METALS

Iron	ppm	50	---	---	---
Copper	ppm	5	---	---	---
Lead	ppm	<1	---	---	---
Tin	ppm	0	---	---	---
Aluminum	ppm	4	---	---	---
Chromium	ppm	0	---	---	---
Molybdenum	ppm	15	---	---	---
Nickel	ppm	<1	---	---	---
Titanium	ppm	0	---	---	---
Silver	ppm	0	---	---	---
Manganese	ppm	<1	---	---	---
Vanadium	ppm	0	---	---	---



### ADDITIVES

Calcium	ppm	377	---	---	---
Magnesium	ppm	203	---	---	---
Zinc	ppm	294	---	---	---
Phosphorus	ppm	413	---	---	---
Barium	ppm	0	---	---	---
Boron	ppm	75	---	---	---

**Depot:** CASKIT  
**Unique No:** 5435539  
**Signed:** Kevin Marson  
**Report Date:** 29 Jul 2022




# CONSTRUCTION EQUIPMENT




## GRAPHS


### Iron (ppm)



### Lead (ppm)



### Aluminum (ppm)




### Chromium (ppm)



### Copper (ppm)



### Silicon (ppm)



### Viscosity @ 40°C



### Additives

