



CONSTRUCTION EQUIPMENT

RG ST-LAURENT VOLVO EC480E 314344 - HYDRAULIC SYSTEM



Sample No: VCP347348
Oil Type: VOLVO SUPER HYDRAULIC OIL 46
Job No:



SAMPLE INFORMATION

Sample Number	VCP347348	VCP380480	VCP347345	VCP394876
Sample Date	15 Aug 2023	08 Aug 2023	08 Aug 2023	11 Jul 2023
Machine Hours	0	0	0	0
Oil Hours	0	0	0	0
Oil Changed	Changed	Changed	N/A	Changed
Sample Status	NORMAL	NORMAL	NORMAL	ABNORMAL

STRONGCO INC

1575 RUE BERSIMIS
 CHICOUTIMI, QC
 CA G7K 1G9
 Contact: Dany Levesque
 dlevesque@strongco.com
 T: (418)690-1724
 F: (418)690-5002



OIL CONDITION

Visc @ 40°C	cSt	45.0	43.6	45.0	43.2
-------------	-----	-------------	------	------	------



CONTAMINATION

Particles >4µm	12280	15970	33230	85723	
Particles >6µm	646	2136	1291	12532	
Particles >14µm	15	67	17	135	
ISO 4406:1999 (c)	21/17/11	21/18/13	22/17/11	24/21/14	
Silicon	ppm	<1	7	1	5
Sodium	ppm	<1	<1	<1	<1
Potassium	ppm	<1	1	<1	1

Diagnosis

Échantillonner de nouveau l'équipement au prochain intervalle de vidange afin d'en surveiller la condition. Les taux d'usure de tous les composants sont normaux. La propreté du système est acceptable pour votre objectif de propreté ISO 4406. La propreté du système et du fluide est acceptable. L'état de l'huile est acceptable pour la durée de service.



WEAR METALS

Iron	ppm	1	3	3	8
Copper	ppm	1	23	2	31
Lead	ppm	0	1	0	2
Tin	ppm	0	<1	0	<1
Aluminum	ppm	<1	<1	<1	<1
Chromium	ppm	0	<1	<1	<1
Molybdenum	ppm	0	0	0	0
Nickel	ppm	<1	0	0	<1
Titanium	ppm	0	0	0	0
Silver	ppm	0	0	0	0
Manganese	ppm	0	0	0	<1
Vanadium	ppm	0	0	0	0



ADDITIVES

Calcium	ppm	50	111	53	83
Magnesium	ppm	<1	<1	0	<1
Zinc	ppm	435	680	448	617
Phosphorus	ppm	360	594	380	564
Barium	ppm	0	0	0	0
Boron	ppm	<1	<1	<1	<1

Depot: VOLVO0230
Unique No: 5629252
Signed: Wes Davis
Report Date: 16 Aug 2023




CONSTRUCTION EQUIPMENT




GRAPHS


Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count

