



CONSTRUCTION EQUIPMENT

W07012289-1 VOLVO A40G 341458 - BOGIE/CENTER RIGHT FINAL DRIVE



Sample No: VCP399853
Oil Type: TRANSAXLE OIL SAE 75W80
Job No: W07012289-1



SAMPLE INFORMATION

Sample Number	VCP399853	---	---	---
Sample Date	23 Feb 2023	---	---	---
Machine Hours	6947	---	---	---
Oil Hours	0	---	---	---
Oil Changed	N/A	---	---	---
Sample Status	ABNORMAL	---	---	---

McClung-Logan Virginia LLC- RICHMOND
1345 MOUNTAIN ROAD
GLEN ALLEN, VA
US 23060
Contact: KYLE RATLIFFE
KRATLIFFE@MCCLUNG-LOGAN.COM
T:
F: (804)266-1611



OIL CONDITION

Visc @ 40°C	cSt	■ 40.7	---	---	---
-------------	-----	--------	-----	-----	-----



CONTAMINATION

Silicon	ppm	■ 18	---	---	---
Sodium	ppm	■ 5	---	---	---
Potassium	ppm	■ <1	---	---	---

Diagnosis

Resample at the next service interval to monitor. The copper level is abnormal. All other component wear rates are normal. Moderate concentration of visible dirt/debris present in the oil. The condition of the oil is acceptable for the time in service.



WEAR METALS

Iron	ppm	■ 50	---	---	---
Copper	ppm	▲ 326	---	---	---
Lead	ppm	■ 1	---	---	---
Tin	ppm	■ 0	---	---	---
Aluminum	ppm	■ 3	---	---	---
Chromium	ppm	■ 1	---	---	---
Molybdenum	ppm	<1	---	---	---
Nickel	ppm	■ 2	---	---	---
Titanium	ppm	<1	---	---	---
Silver	ppm	<1	---	---	---
Manganese	ppm	■ 2	---	---	---
Vanadium	ppm	■ 0	---	---	---



ADDITIVES


Calcium	ppm	■ 3931	---	---	---
Magnesium	ppm	■ 15	---	---	---
Zinc	ppm	■ 1534	---	---	---
Phosphorus	ppm	■ 1214	---	---	---
Barium	ppm	<1	---	---	---
Boron	ppm	■ 143	---	---	---

Depot: VOLVO8882
Unique No: 10351076
Signed: Angela Borella
Report Date: 27 Feb 2023




GRAPHS

Ferrous Alloys



▲ Non-ferrous Metals



Viscosity @ 40°C

