

CONSTRUCTION EQUIPMENT X58294 VOLVO EC250ELR 316395 - DIESEL ENGINE



Sample No: VCP413486
Oil Type: NOT GIVEN
Job No: X58294

SAMPLE	INFORMATION			
Sample Number	-	VCP413486	 	
Sample Date		20 Jul 2023	 	
Machine Hours		193	 	
Oil Hours		0	 	
Oil Changed		Changed	 	
Sample Status		ABNORMAL	 	
OIL CON	DITION			
Visc @ 100°C	cSt	▲ 11.1	 	
Base Number (BN	I) mg KOH/g	■7.4	 	
Oxidation (PA)	%	55	 	
CONTAM	IINATION			
Soot %	%	0.1	 	
Nitration (PA)	%	68	 	
Sulfation (PA)	%	49	 	
Glycol	%	NEG	 	
Fuel	%	0.4	 	
Silicon	ppm	■23	 	
Sodium	ppm	■ 4	 	
Potassium	ppm	6	 	
WEAR M	IETALS			
Iron	ppm	■ 9	 	
Copper	ppm	118	 	
Lead	ppm	2	 	
Tin	ppm	■ <1	 	
Aluminum	ppm	■ 4	 	
Chromium	ppm	■ <1	 	
Molybdenum	ppm	■86	 	
Nickel	ppm	■<1	 	
Titanium	ppm	<1	 	
Silver	ppm	■<1	 	
Manganese	ppm	1	 	
Vanadium	ppm	<1	 	
VOLVO				
ADDITIV	ES			
Calcium	ppm	2194	 	
Magnesium	ppm	22	 	
Zinc	ppm	1173	 	
Phosphorus	ppm	■992	 	
Barium	ppm	■0	 	



SCOTT EQUIPMENT COMPANY LLC - Saint Rose PO BOX 997 SAINT BOSE LA

SAINT ROSE, LA US 70087

Contact: DENISE CORVERS dcorvers@scottcompanies.com

T: (504)461-0961 F: (504)461-0970

Diagnosis

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor. The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other metal levels are typical for a new component breaking in. Tests indicate that there is no fuel present in the oil. There is no indication of any contamination in the oil. The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

Depot:SCOSAIUnique No:10573013Signed:Sean FeltonReport Date:27 Jul 2023

ppm

Boron



CONSTRUCTION EQUIPMENT





