

Sample No: VCP383306

Oil Type: MOBIL MOBILFLUID 424

Job No: SW1-22210 SIMPLY NAT

SAMPLE	INFORMATION	N			
Sample Number		VCP383306			
Sample Date		27 Jul 2023			
Machine Hours		10458			
Oil Hours		0			
Oil Changed		Changed			
Sample Status		NORMAL			
OIL CONDITION					
Visc @ 40°C	cSt	<b>52.1</b>			
Vise & 10 C	COL				
VOLVO					
LONIAM	IINATION				
Silicon	ppm	<b>24</b>			
Sodium	ppm	<b>1</b>			
Potassium	ppm	<b>0</b>			
VOLVO					
WEAR METALS					
Iron	ppm	<b>105</b>			
Copper	ppm	<b>■&lt;1</b>			
Lead	ppm	■0			
Tin	ppm	■0			
Aluminum	ppm	<b>2</b>			
Chromium	ppm	■2			
Molybdenum	ppm	<b>14</b>			
Nickel	ppm	<b>■&lt;1</b>			
Titanium	ppm	<1			
Silver	ppm	0			
Manganese	ppm	<b>12</b>			
Vanadium	ppm	0			
VOLVO					
ADDITIV	ES				
Calcium	ppm	■3602			
Magnesium	ppm	■31			
Zinc	ppm	<b>1509</b>			
Phosphorus	ppm	<b>1176</b>			
Barium	ppm	■0			
Boron	ppm	<b>116</b>			



## ARNOLD MACHINERY COMPANY

464 WASHINGTON STREET S TWIN FALLS, ID US 83301 Contact: JANAE HYMAS jhymas@arnoldmachinery.com T: (208)733-1715 F: (775)356-7152

## Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:VOLVO1835Unique No:10585680Signed:Wes DavisReport Date:03 Aug 2023



## **CONSTRUCTION EQUIPMENT**





