

CONSTRUCTION EQUIPMENT
SWA335274 MEIJER MIO DS00100 100KW 0414 - DIESEL ENGIN

Sample No: VCP380680 Oil Type: **NOT GIVEN**

Job No: SWA335274 MEIJER

SAMPLE IN	FORMATION			
Sample Number		VCP380680	 	
Sample Date		16 Aug 2023	 	
Machine Hours		375	 	
Oil Hours		0	 	
Oil Changed		N/A	 	
Sample Status		NORMAL	 	
OIL CONDI	TION			
Visc @ 100°C	cSt	13.9	 	
Base Number (BN)	mg KOH/g	■9.6	 	
Oxidation (PA)	%	54	 	
CONTAMIN	IATION			
Soot %	%	0.3	 	

CONTAMINATION						
Soot %	%	■0.3				
Nitration (PA)	%	47				
Sulfation (PA)	%	49				
Glycol	%	NEG				
Fuel	%	<1.0				
Silicon	ppm	■4				
Sodium	ppm	■<1				
Potassium	ppm	■<1				

WEAR N	METALS			
Iron	ppm	17	 	
Copper	ppm	1	 	
Lead	ppm	■ <1	 	
Tin	ppm	■ <1	 	
Aluminum	ppm	2	 	
Chromium	ppm	■<1	 	
Molybdenum	ppm	73	 	
Nickel	ppm	■ <1	 	
Titanium	ppm	0	 	
Silver	ppm	■ 0	 	
Manganese	ppm	<1	 	
Vanadium	ppm	0	 	

ADDITIVES					
Calcium	ppm	1251			
Magnesium	ppm	■1126			
Zinc	ppm	1451			
Phosphorus	ppm	1242			
Barium	ppm	■ 0			
Boron	ppm	■3			



ALTA CONSTRUCTION EQUIPMENT LLC

G-3283 S. DORT HIGHWAY BURTON, MI US 48529 Contact: BURTON SERVICE BURTON.SERVICE@ALTAEQUIPMENT.COM

F:

Diagnosis

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.Metal levels are typical for a new component breaking in. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Depot: VOLVO5023 **Unique No:** 10630062 Signed: Wes Davis Report Date: 31 Aug 2023



CONSTRUCTION EQUIPMENT





