

CONSTRUCTION EQUIPMENT VOLVO A40G 353407 - DIESEL ENGINE



Sample No: VCP312575
Oil Type: MOBIL 15W40

Job No:

SAMPLE II	NFORMATION			
Sample Number		VCP312575	 	
Sample Date		03 Oct 2023	 	
Machine Hours		504	 	
Oil Hours		504	 	
Oil Changed		Changed	 	
Sample Status		ABNORMAL	 	
OIL CONDI	TION			
Visc @ 100°C	cSt	<u> </u>	 	
Base Number (BN)		■ 5.7	 	
Oxidation (PA)	%	56	 	
CONTAMIN	MATION			
_				
Soot %	%	■ 0.2	 	
Nitration (PA)	%	78	 	
Sulfation (PA) Glycol	%	51 NEG	 	
Fuel	%	■ 0.5	 	
Silicon	ppm	■ 0.3	 	
Sodium	ppm	4	 	
Potassium	ppm	<u>5</u>	 	
	I. I.			
WEAR ME	TALC			
_	IMT7			
lron -	ppm	22	 	
Copper	ppm	<u>^</u> 425	 	
Lead	ppm	■ <1	 	
Tin Aluminum	ppm	□ 3 □ 4	 	
Chromium	ppm	= 4	 	
Molybdenum	ppm ppm	■87	 	
Nickel	ppm	2	 	
Titanium	ppm	<1	 	
Silver	ppm	0	 	
Manganese	ppm	■3	 	
Vanadium	ppm	0	 	
ADDITIVE:	S			
Calcium	ppm	2122	 	
Magnesium	ppm	48	 	
Zinc	ppm	1189	 	
Phosphorus	ppm	1030	 	
Barium	ppm	0	 	
Boron	ppm	43	 	



SCHILDBERG CONSTRUCTION COMPANY

PO BOX 358 GREENFIELD, IA US 50849 Contact: SCOTT ARMSTRONG sarmstrong@schildberg.com T: (641)743-8237 F: (641)743-2486

Diagnosis

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor. The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other metal levels are typical for a new component breaking in. Fuel content negligible. There is no indication of any contamination in the oil. The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

Depot:SCHGREUnique No:10700642Signed:Don BaldridgeReport Date:20 Oct 2023



CONSTRUCTION EQUIPMENT





GRAPHS

