



CONSTRUCTION EQUIPMENT

2632-1 ESTES VOLVO A30C 2380 - DIESEL ENGINE



Sample No: VCP441111
Oil Type: DIESEL ENGINE OIL SAE 40
Job No: 2632-1 ESTES



SAMPLE INFORMATION

Sample Number	VCP441111	---	---	---
Sample Date	01 Nov 2023	---	---	---
Machine Hours	15371	---	---	---
Oil Hours	0	---	---	---
Oil Changed	N/A	---	---	---
Sample Status	NORMAL	---	---	---

MCLLUNG-LOGAN EQUIPMENT CO - WISE
PO BOX 1158
WISE, VA
US 24293
Contact: DANNY BARRINGTON
dbarrington@mcclung-logan.com
T:
F:



OIL CONDITION

Visc @ 100°C	cSt	█ 13.2	---	---	---
Base Number (BN)	mg KOH/g	█ 10.7	---	---	---
Oxidation (PA)	%	73	---	---	---

Diagnosis

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DIESEL ENGINE OIL SAE 40. Please confirm.

All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



CONTAMINATION

Soot %	%	█ 0.1	---	---	---
Nitration (PA)	%	41	---	---	---
Sulfation (PA)	%	58	---	---	---
Glycol	%	NEG	---	---	---
Fuel	%	<1.0	---	---	---
Silicon	ppm	█ 6	---	---	---
Sodium	ppm	█ <1	---	---	---
Potassium	ppm	█ <1	---	---	---



WEAR METALS

Iron	ppm	█ 7	---	---	---
Copper	ppm	█ 8	---	---	---
Lead	ppm	█ 23	---	---	---
Tin	ppm	█ 2	---	---	---
Aluminum	ppm	█ 4	---	---	---
Chromium	ppm	█ <1	---	---	---
Molybdenum	ppm	█ 38	---	---	---
Nickel	ppm	█ <1	---	---	---
Titanium	ppm	█ 0	---	---	---
Silver	ppm	█ 0	---	---	---
Manganese	ppm	█ <1	---	---	---
Vanadium	ppm	0	---	---	---



ADDITIVES

Calcium	ppm	█ 1561	---	---	---
Magnesium	ppm	█ 551	---	---	---
Zinc	ppm	█ 1146	---	---	---
Phosphorus	ppm	█ 949	---	---	---
Barium	ppm	█ 0	---	---	---
Boron	ppm	█ 67	---	---	---

Depot: VOLVO8881
Unique No: 10726920
Signed: Wes Davis
Report Date: 06 Nov 2023



CONSTRUCTION EQUIPMENT




GRAPHS


Iron (ppm)




Lead (ppm)




Aluminum (ppm)




Chromium (ppm)



Copper (ppm)



Silicon (ppm)



Viscosity @ 100°C



Base Number

