

CONSTRUCTION EQUIPMENT VOLVO A60H 340039 - BOGIE/CENTER AXLE



Sample No: VCP441431

Oil Type: GEAR OIL SAE 80W140

Job No:

SAMPLE	INFORMATION				
Sample Number	_	VCP441431	VCP428977	VCP412574	VCP366096
Sample Date		18 Jan 2024	27 Sep 2023	20 Jun 2023	29 Nov 2022
Machine Hours		8521	8052	7542	7061
Oil Hours		0	0	0	0
Oil Changed		Not Changd	Changed	Not Changd	Not Changd
Sample Status		NORMAL	NORMAL	NORMAL	NORMAL
OIL CON	DITION				
Visc @ 40°C	cSt	283	271	270	271
VOLVO					
CONTAN	MINATION				
Water	%	NEG	NEG	NEG	NEG
Silicon	ppm	■3	2	1 2	1 2
Sodium	ppm	2	□ <1	□ <1	□ <1
Potassium	ppm	□ <1	<1	0	0
Otassiaiii	ррш				
VOLVO	477016				
WEAR N	METALS				
Iron	ppm	9	■31	■39	1 7
Copper	ppm	■0	- <1	0	- <1
Lead	ppm	0		0	0
Tin	ppm	■0	- <1		0
Aluminum	ppm	■0	0	■ 0	- <1
Chromium	ppm	■0		1	- <1
Molybdenum	ppm	6	2	2	2
Nickel	ppm	■<1	0		0
Titanium	ppm	0	0	0	0
Silver	ppm	0	0	0	0
Manganese	ppm	■ <1	1	1	- <1
Vanadium	ppm	0	0	0	0
VOLVO					
ADDITIV	IES				
Calcium	ppm	101	7 6	■86	7 4
Magnesium	ppm	33	11	■ 15	11
Zinc	ppm	■95	2 7	1 45	1 43
Phosphorus	ppm	756	916	□ 1017	844
Barium	ppm	= <1	0	0	0
Boron	ppm	■132	145	■ 182	145
201011	PPIII		175		<u> </u>

SAIIA CONSTRUCTION LLC

4400 LEWISBURG RD BIRMINGHAM, AL US 35207

Contact: STEPHANI BRITTON sbritton@saiia.com;doug.bogart@wearcheck.com

T: (205)943-2268 F: (205)943-2269

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:SAIBIRUnique No:10848657Signed:Sean FeltonReport Date:30 Jan 2024



CONSTRUCTION EQUIPMENT





