


CONSTRUCTION EQUIPMENT

G60879 FBS TIRE VOLVO L120F 25666 - HYDRAULIC SYSTEM



Oil Type: AW HYDRAULIC OIL ISO 46

Job No: G60879 FBS TIRE

SAMPLE	INFORMATION			
Sample Number	-	VCE73744	 	
Sample Date		24 Jan 2024	 	
Machine Hours		26539	 	
Oil Hours		0	 	
Oil Changed		Not Changd	 	
Sample Status		NORMAL	 	
VOLVO	ITION			
OIL COND				<u> </u>
Visc @ 40°C	cSt	44.2	 	
Acid Number (AN)	mg KOH/g	■0.35	 	
VOLVO				
CONTAM	INATION			
Water	%	NEG	 	
Particles >4µm	70	18224	 	
•		■ 1760	 	
Particles > 6µm Particles > 14µm		■ 1760 ■ 64	 	
•		_	 	
ISO 4406:1999 (c)		21/18/13	 	
Silicon Sodium	ppm	1	 	
	ppm		 	
Potassium	ppm	■0	 	
VOLVO				
WEAR MI	ETALS			
Iron	ppm	□ 4	 	
Copper	ppm	<u></u> 2	 	
Lead	ppm	■0	 	
Tin	ppm	■0	 	
Aluminum	ppm	■ 0	 	
Chromium	ppm	■0	 	
Molybdenum	ppm	■0	 	
Nickel	ppm	■0	 	
Titanium	ppm	<1	 	
Silver	ppm	0	 	
Manganese	ppm	0	 	
Vanadium	ppm	0	 	
VOLVO				
ADDITIVE ADDITIVE	7			
Calcium	ppm	■89	 	
Magnesium	ppm	■0	 	



CHADWICK-BAROSS INC

ROUTE106 237 SHEEP DAVIS ROAD CONCORD, NH US 03301 Contact: DOMINIC RUGGIERO ruggiero@chadwick-baross.com T: F: (603)224-3001

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Depot:VOLVO0049Unique No:10855902Signed:Wes DavisReport Date:31 Jan 2024

ppm

ppm

ppm

ppm

442

332

0

0

Zinc

Barium

Boron

Phosphorus



CONSTRUCTION EQUIPMENT





GRAPHS

