



CONSTRUCTION EQUIPMENT

SWA471617 SANCAP ASV RT-75 ASVRT075TPDH004935 - DIESEL ENGINE



Sample No: VCP441193
Oil Type: {unknown}
Job No: SWA471617 SANCAP



SAMPLE INFORMATION

Sample Number	VCP441193	---	---	---
Sample Date	02 Feb 2024	---	---	---
Machine Hours	37	---	---	---
Oil Hours	0	---	---	---
Oil Changed	Changed	---	---	---
Sample Status	NORMAL	---	---	---

ALTA EQUIPMENT COMPANY
5151 DR MARTIN LUTHER KING BLVD
FORT MYERS, FL
US 33905
Contact: TODD LARK
tlark@altaequipfl.com
T:
F: (239)481-3302



OIL CONDITION

Visc @ 100°C	cSt	█ 13.6	---	---	---
Base Number (BN)	mg KOH/g	█ 9.4	---	---	---
Oxidation (PA)	%	60	---	---	---

Diagnosis

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. Metal levels are typical for a new component breaking in. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



CONTAMINATION

Water	%	NEG	---	---	---
Soot %	%	█ 0	---	---	---
Nitration (PA)	%	53	---	---	---
Sulfation (PA)	%	49	---	---	---
Glycol	%	NEG	---	---	---
Fuel	%	<1.0	---	---	---
Silicon	ppm	█ 20	---	---	---
Sodium	ppm	█ 4	---	---	---
Potassium	ppm	█ 2	---	---	---



WEAR METALS

Iron	ppm	█ 14	---	---	---
Copper	ppm	█ 8	---	---	---
Lead	ppm	█ 0	---	---	---
Tin	ppm	█ <1	---	---	---
Aluminum	ppm	█ 3	---	---	---
Chromium	ppm	█ <1	---	---	---
Molybdenum	ppm	█ 56	---	---	---
Nickel	ppm	█ 0	---	---	---
Titanium	ppm	0	---	---	---
Silver	ppm	█ 0	---	---	---
Manganese	ppm	2	---	---	---
Vanadium	ppm	0	---	---	---



ADDITIVES

Calcium	ppm	█ 878	---	---	---
Magnesium	ppm	█ 1005	---	---	---
Zinc	ppm	█ 1251	---	---	---
Phosphorus	ppm	█ 1061	---	---	---
Barium	ppm	█ 8	---	---	---
Boron	ppm	█ 58	---	---	---

Depot: VOLVO0090
Unique No: 10875350
Signed: Wes Davis
Report Date: 14 Feb 2024



CONSTRUCTION EQUIPMENT



GRAPHS


Iron (ppm)




Lead (ppm)



Aluminum (ppm)




Chromium (ppm)



Copper (ppm)



Silicon (ppm)



Viscosity @ 100°C



Base Number

