

CONSTRUCTION EQUIPMENT VOLVO A40G 353407 - BOGIE/CENTER AXLE



Sample No: VCP416164

Oil Type: MOBIL MOBILUBE HD 80W90

Report Id: SCHGRE [WUSCAR] 06100428 (Generated: 02/28/2024 12:59:04) Rev: 1

Job No:

CAMPI	E INFORMATION				
Sample Number	- IIII OIII III IIII	VCP416164	VCP378569	VCP312576	
Sample Date		25 Feb 2024	14 Dec 2023	03 Oct 2023	
Machine Hours		1268	997	504	
Oil Hours		871	600	504	
Oil Changed		Changed	Not Changd	Not Changd	
Sample Status		ATTENTION	ATTENTION	ABNORMAL	
Sample Status		ATTENTION	ATTENTION	ADNORIVIAL	
VOLVO					
OIL CON	DITION				
Visc @ 40°C	cSt	<u>▲</u> 51.9	▲ 51.8	▲ 52.2	
VOLVO	MINATION				
_	MINATION				
Water	%	NEG	NEG	NEG	
Silicon	ppm	■3	2	2	
Sodium	ppm	2	 <1	0	
Potassium	ppm	6	5	6	
WEAR N	METALS				
_		= 226	 404	— 100	
Iron	ppm	206	101	■ 100	
Copper	ppm	3	- <1	2	
Lead	ppm	- <1	0	0	
Tin	ppm	■0	0	0	
Aluminum	ppm	■ <1	0	1	
Chromium	ppm	2	= <1	1	
Molybdenum	ppm	■2	0	2	
Nickel	ppm	■1	0	 <1	
Titanium	ppm	0	0	0	
Silver	ppm	0	0	0	
Manganese	ppm	■7	5	4	
Vanadium	ppm	0	0	0	
VOLVO					
ADDITIV	VES				
Calcium	-	— 30	1 4	T 16	
	ppm	38	14	4 6	
Magnesium	ppm	□ 2	0	1	
Zinc	ppm	_	7	■ 8	
Phosphorus	ppm	2247	2198	2254	
Barium	ppm	0	0	0	
Boron	ppm	253	■246	□284	



SCHILDBERG CONSTRUCTION COMPANY

PO BOX 358 GREENFIELD, IA US 50849 Contact: SCOTT ARMSTRONG sarmstrong@schildberg.com T: (641)743-8237 F: (641)743-2486

Diagnosis

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The oil viscosity is lower than normal. Confirm oil type.

Depot:SCHGREUnique No:10898658Signed:Jonathan HesterReport Date:28 Feb 2024



CONSTRUCTION EQUIPMENT





