Sample No: VCP442464
Oil Type: {unknown}

Job No: SW-29953 SEG 1 RANGO

CVWDIE	INFORMATION	η		
	INFURMATION		_	
Sample Number		VCP442464		
Sample Date		26 Feb 2024		
Machine Hours		3292		
Oil Hours		0		
Oil Changed		Not Changd		
Sample Status		NORMAL		
OIL CON	DITION			
Visc @ 40°C	cSt	51.5		
	CSt	31.3		
VOLVO				
CONTAN	MINATION			
Water	%	NEG		
Silicon	ppm	18		
Sodium	ppm	■ 0		
Potassium	ppm	■0		
VOLVO	AFTALC			
WEAR N	JE I ALS			
Iron	ppm	■9		
Copper	ppm	■87		
Lead	ppm	1		
Tin	ppm	■0		
Aluminum	ppm	2		
Chromium	ppm	■0		
Molybdenum	ppm	0		
Nickel	ppm	■ 4		
Titanium	ppm	0		
Silver	ppm	0		
Manganese	ppm	0		
Vanadium	ppm	0		
ADDITIV	/FS			
_		4405		
Calcium 	ppm	1105		
Magnesium	ppm	4		
Zinc	ppm	449		
Phosphorus	ppm	540		
Barium	ppm	0		
Boron	ppm	<1		

ARNOLD MACHINERY COMPANY

2975 WEST 2100 SOUTH
SALT LAKE CITY, UT
US 84119
Contact: TONY PAYAN
tpayan@arnoldmachinery.com
T: (801)972-4000
F: (801)975-9434

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:VOLVO8770Unique No:10903732Signed:Don BaldridgeReport Date:04 Mar 2024



CONSTRUCTION EQUIPMENT





