



CONSTRUCTION EQUIPMENT

701243 HERC VOLVO L70H 625244 - DIESEL ENGINE



Sample No: VCP443797
Oil Type: DIESEL ENGINE OIL SAE 15W40
Job No: 701243 HERC



ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC
 8418 PALM RIVER ROAD
 TAMPA, FL
 US 33619
 Contact: KENNY HANEY
 khaney@flaglerce.com
 T: (813)630-0077
 F: (813)630-2233



SAMPLE INFORMATION

Sample Number	VCP443797	---	---	---
Sample Date	08 Apr 2024	---	---	---
Machine Hours	871	---	---	---
Oil Hours	0	---	---	---
Oil Changed	Changed	---	---	---
Sample Status	NORMAL	---	---	---



OIL CONDITION

Visc @ 100°C	cSt	█ 12.7	---	---	---
Base Number (BN)	mg KOH/g	█ 8.8	---	---	---
Oxidation (PA)	%	77	---	---	---



CONTAMINATION

Water	%	NEG	---	---	---
Soot %	%	█ 0.3	---	---	---
Nitration (PA)	%	71	---	---	---
Sulfation (PA)	%	59	---	---	---
Glycol	%	NEG	---	---	---
Fuel	%	<1.0	---	---	---
Silicon	ppm	█ 20	---	---	---
Sodium	ppm	█ 3	---	---	---
Potassium	ppm	█ 2	---	---	---



WEAR METALS

Iron	ppm	█ 34	---	---	---
Copper	ppm	█ 10	---	---	---
Lead	ppm	█ 2	---	---	---
Tin	ppm	█ 5	---	---	---
Aluminum	ppm	█ 22	---	---	---
Chromium	ppm	█ 3	---	---	---
Molybdenum	ppm	█ 48	---	---	---
Nickel	ppm	█ 2	---	---	---
Titanium	ppm	█ <1	---	---	---
Silver	ppm	█ <1	---	---	---
Manganese	ppm	█ 6	---	---	---
Vanadium	ppm	<1	---	---	---



ADDITIVES

Calcium	ppm	█ 1602	---	---	---
Magnesium	ppm	█ 530	---	---	---
Zinc	ppm	█ 1166	---	---	---
Phosphorus	ppm	█ 1061	---	---	---
Barium	ppm	█ 3	---	---	---
Boron	ppm	█ 52	---	---	---

Diagnosis

Resample at the next service interval to monitor. Metal levels are typical for a new component breaking in. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Depot: VOLVO0093
Unique No: 10982793
Signed: Wes Davis
Report Date: 18 Apr 2024




CONSTRUCTION EQUIPMENT



GRAPHS


Iron (ppm)




Lead (ppm)




Aluminum (ppm)




Chromium (ppm)




Copper (ppm)



Silicon (ppm)



Viscosity @ 100°C



Base Number

