

# CONSTRUCTION EQUIPMENT VOLVO A45G 752257 - HYDRAULIC SYSTEM



Sample No: VCP371017

Oil Type: VOLVO SUPER HYDRAULIC OIL 46

Job No:

VOLVO				
SAMPLE IN	NFORMATION			
Sample Number	•	VCP371017	 	
Sample Date		08 Apr 2024	 	
Machine Hours		196	 	
Oil Hours		196	 	
Oil Changed		Changed	 	
Sample Status		NORMAL	 	
VOINO OIL CONDI	TION			
OIL CONDI				
Visc @ 40°C	cSt	<b>47.5</b>	 	
Acid Number (AN)	mg KOH/g	<b>0.48</b>	 	
CONTAMIN	IATION			
Water	%	NEG	 	
Particles >4µm	70	5161	 	
Particles >6µm		■ 1426	 	
Particles > 14µm		■ 1420 ■ 50	 	
ISO 4406:1999 (c)		20/18/13	 	
Silicon	nnm	20/18/13	 	
Sodium	ppm	<b>■</b> < 1	 	
Potassium	ppm	<b>1</b>	 	
rotassiuiii	ppm		 	
VOLVO				
WEAR ME	TALS			
Iron	ppm	<b>■</b> <1	 	
Copper	ppm	<b>2</b>	 	
Lead	ppm	<b>1</b>	 	
Tin	ppm	<b>■&lt;1</b>	 	
Aluminum	ppm	<b>2</b>	 	
Chromium	ppm	<b>■&lt;1</b>	 	
Molybdenum	ppm	<b>■&lt;1</b>	 	
Nickel	ppm	<b>■&lt;1</b>	 	
Titanium	ppm	<1	 	
Silver	ppm	0	 	
Manganese	ppm	<b>■&lt;1</b>	 	
Vanadium	ppm	<1	 	
ADDITIVES	7			
_				
Calcium	ppm	<b>69</b>	 	
Magnesium	ppm	<b>■</b> <1	 	
Zinc	ppm	<b>■</b> 587	 	
Phosphorus	ppm	<b>□</b> 476	 	
Barium	ppm	0	 	
Boron	ppm	<b>□</b> 0	 	



### THE GW VAN KEPPEL CO MAIN

1801 NORTH 9TH STREET KANSAS CITY, KS US 66101 Contact: BRIAN LODERHOSE bloderhose@vankeppel.com T:

F: (913)281-4815

## Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

 Depot:
 VOLVO0111

 Unique No:
 10993854

 Signed:
 Wes Davis

 Report Date:
 24 Apr 2024



# **CONSTRUCTION EQUIPMENT**





#### GRAPHS

