



CONSTRUCTION EQUIPMENT

BARTOW U PULL YARD VOLVO L70H 622588 - DIESEL ENGINE



Sample No: VCP451353
Oil Type: VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3
Job No: BARTOW U PULL YARD



ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC
 8418 PALM RIVER ROAD
 TAMPA, FL
 US 33619
 Contact: KENNY HANEY
 khaney@flaglerce.com
 T: (813)630-0077
 F: (813)630-2233



SAMPLE INFORMATION

Sample Number	VCP451353	---	---	---
Sample Date	20 May 2024	---	---	---
Machine Hours	5275	---	---	---
Oil Hours	0	---	---	---
Oil Changed	Changed	---	---	---
Sample Status	ABNORMAL	---	---	---



OIL CONDITION

Visc @ 100°C	cSt	█ 13.0	---	---	---
Base Number (BN)	mg KOH/g	█ 8.0	---	---	---
Oxidation (PA)	%	55	---	---	---



CONTAMINATION

Water	%	NEG	---	---	---
Soot %	%	█ 0.1	---	---	---
Nitration (PA)	%	43	---	---	---
Sulfation (PA)	%	55	---	---	---
Glycol	%	NEG	---	---	---
Fuel	%	<1.0	---	---	---
Silicon	ppm	█ 5	---	---	---
Sodium	ppm	█ 2	---	---	---
Potassium	ppm	█ 3	---	---	---



WEAR METALS

Iron	ppm	█ 8	---	---	---
Copper	ppm	█ 0	---	---	---
Lead	ppm	█ <1	---	---	---
Tin	ppm	█ <1	---	---	---
Aluminum	ppm	▲ 12	---	---	---
Chromium	ppm	█ 0	---	---	---
Molybdenum	ppm	█ 96	---	---	---
Nickel	ppm	█ <1	---	---	---
Titanium	ppm	0	---	---	---
Silver	ppm	█ 0	---	---	---
Manganese	ppm	█ <1	---	---	---
Vanadium	ppm	<1	---	---	---



ADDITIVES

Calcium	ppm	█ 1374	---	---	---
Magnesium	ppm	█ 458	---	---	---
Zinc	ppm	█ 1103	---	---	---
Phosphorus	ppm	█ 967	---	---	---
Barium	ppm	█ 0	---	---	---
Boron	ppm	█ 470	---	---	---

Diagnosis

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. The aluminum level is abnormal. All other component wear rates are normal. There is no indication of any contamination in the oil. The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

Depot: VOLVO0093
Unique No: 11050440
Signed: Sean Felton
Report Date: 30 May 2024




CONSTRUCTION EQUIPMENT



GRAPHS

Iron (ppm)



Lead (ppm)




Aluminum (ppm)




Chromium (ppm)



Copper (ppm)



Silicon (ppm)



Viscosity @ 100°C



Base Number

