

CONSTRUCTION EQUIPMENT 42325 VOLVO A30G 752350 - BRAKE



Sample No: VCP447884

Oil Type: VOLVO SUPER WET BRAKE TRANSAXLE OIL WB102

Job No: 42325

SAMPLE	INFORMATION			
Sample Number	_	VCP447884	 	
Sample Date		07 Jun 2024	 	
Machine Hours		2456	 	
Oil Hours		0	 	
Oil Changed		Not Changd	 	
Sample Status		ABNORMAL	 	
		71211011111111		
OIL CON	NITION			
Visc @ 40°C	cSt	= 46.5		
	CST	46.5	 	
CONTAN				
CONTAM	IINATION			
Water	%	NEG	 	
Silicon	ppm	■10	 	
Sodium	ppm	7	 	
Potassium	ppm	<u></u> 5	 	
Otassiaiii	PPIII			
VOLVO				
WEAR M	IETALS			
Iron	ppm	26	 	
Copper	ppm	253	 	
Lead	ppm	5	 	
Tin	ppm	2	 	
Aluminum	ppm	1	 	
Chromium	ppm	■ <1	 	
Molybdenum	ppm	■ 3	 	
Nickel	ppm	■<1	 	
Titanium	ppm	0	 	
Silver	ppm	0	 	
Manganese	ppm	2	 	
Vanadium	ppm	0	 	
ADDITIV	ES			
Calcium	ppm	2970	 	
Magnesium	ppm	■12	 	
Zinc	ppm	1253	 	
Phosphorus	ppm	■ 1070	 	
Barium	ppm	0	 	
Boron	ppm	■80	 	
201011	PPIII			



215 - ASCENDUM MACHINERY INC - CAYCE
2303 AIRPORT BLVD
CAYCE, SC
US 29033
Contact: GARY MARTIN
GARY.MARTIN@ASCENDUMMACHINERY.COM
T: (803)727-9615

Diagnosis

F: (803)791-9920

No corrective action is recommended at this time. Resample at the next service interval to monitor. The copper level is abnormal. All other component wear rates are normal. There is no indication of any contamination in the fluid. The condition of the fluid is acceptable for the time in service.

Depot:VOLVO0013Unique No:11074397Signed:Don BaldridgeReport Date:13 Jun 2024



CONSTRUCTION EQUIPMENT





