



CONSTRUCTION EQUIPMENT

729854 SEMINOLE CO VOLVO EC480 314333 - HYDRAULIC SYSTEM



Sample No: VCP454579
Oil Type: VOLVO SUPER HYDRAULIC OIL 46
Job No: 729854 SEMINOLE CO



ALTA EQUIPMENT/FLAGLER EQUIPMENT LLC
 9601 BOGGY CREEK RD
 ORLANDO, FL
 US 32824
 Contact: Robert LaPlante
 robert.laplante@altg.com
 T: (407)508-9736
 F: (407)659-8720



SAMPLE INFORMATION

Sample Number	VCP454579	VCP395926	---	---
Sample Date	13 Jun 2024	16 Jan 2023	---	---
Machine Hours	3604	3550	---	---
Oil Hours	0	0	---	---
Oil Changed	Not Chngd	Not Chngd	---	---
Sample Status	NORMAL	ABNORMAL	---	---



OIL CONDITION

Visc @ 40°C	cSt	█ 41.2	█ 40.8	---	---
Acid Number (AN)	mg KOH/g	█ 0.28	█ 0.61	---	---



CONTAMINATION

Water	%	NEG	▲ 0.221	---	---
Particles >4µm		█ 14440	---	---	---
Particles >6µm		█ 1833	---	---	---
Particles >14µm		█ 31	---	---	---
ISO 4406:1999 (c)		21/18/12	---	---	---
Silicon	ppm	█ 5	█ 13	---	---
Sodium	ppm	█ 3	█ 3	---	---
Potassium	ppm	█ 4	█ 4	---	---



WEAR METALS

Iron	ppm	█ 8	█ 5	---	---
Copper	ppm	█ 24	█ 10	---	---
Lead	ppm	█ 0	█ <1	---	---
Tin	ppm	█ <1	█ <1	---	---
Aluminum	ppm	█ 1	█ 6	---	---
Chromium	ppm	█ 1	█ <1	---	---
Molybdenum	ppm	█ 0	█ 10	---	---
Nickel	ppm	█ 0	█ 0	---	---
Titanium	ppm	0	<1	---	---
Silver	ppm	0	<1	---	---
Manganese	ppm	█ <1	█ <1	---	---
Vanadium	ppm	0	0	---	---



ADDITIVES

Calcium	ppm	█ 64	634	---	---
Magnesium	ppm	█ 4	█ 33	---	---
Zinc	ppm	█ 428	█ 614	---	---
Phosphorus	ppm	█ 392	█ 491	---	---
Barium	ppm	█ 0	█ 1	---	---
Boron	ppm	█ 0	█ 12	---	---

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Depot: VOLVO0096
Unique No: 11096291
Signed: Wes Davis
Report Date: 25 Jun 2024




CONSTRUCTION EQUIPMENT




GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number

