Sample No: VCP454092

Oil Type: VOLVO SUPER HYDRAULIC OIL 46

Job No: SW-36287-2 GRANT MAC

SAMPLE II	NFORMATION				
Sample Number	-	VCP454092			
Sample Date		19 Jun 2024			
Machine Hours		2065			
Oil Hours		2065			
Oil Changed		Not Changd			
Sample Status		NORMAL			
OIL CONDITION					
Visc @ 40°C		= 44.1			
	cSt	44.1			
Acid Number (AN)	mg KOH/g	0.64			
VOLVO					
CONTAMI	NATION				
Water	%	NEG			
Particles >4µm		■982			
Particles >6µm		115			
Particles > 14µm		8			
ISO 4406:1999 (c)		17/14/10			
Silicon	ppm	■5			
Sodium	ppm	<u> </u>			
Potassium	ppm	0			
		_			
VOLVO WEAD ME	TALC				
WEAR ME	IAL2				
Iron	ppm	■ 3			
Copper	ppm	■38			
Lead	ppm	■0			
Tin	ppm	■ 0			
Aluminum	ppm	■0			
Chromium	ppm	■ 0			
Molybdenum	ppm	■0			
Nickel	ppm	■0			
Titanium	ppm	0			
Silver	ppm	0			
Manganese	ppm	 <1			
Vanadium	ppm	0			
VOLVO					
ADDITIVE:	5				
Calcium	ppm	100			
Magnesium	ppm	□ 0			
Zinc	ppm	■ 622			
Phosphorus	ppm	499			
Parium	PPIII	- 0			

ARNOLD MACHINERY COMPANY

2975 WEST 2100 SOUTH
SALT LAKE CITY, UT
US 84119
Contact: TONY PAYAN
tpayan@arnoldmachinery.com
T: (801)972-4000
F: (801)975-9434

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Depot:VOLVO8770Unique No:11100477Signed:Wes DavisReport Date:28 Jun 2024

ppm

ppm

Barium

Boron



CONSTRUCTION EQUIPMENT





GRAPH

