



CONSTRUCTION EQUIPMENT

VOLVO EC950FL 410168 - HYDRAULIC SYSTEM



Sample No: VCP445710
Oil Type: VOLVO SUPER HYDRAULIC OIL 46
Job No:



SAMPLE INFORMATION

Sample Number	VCP445710	VCP446912	---	---
Sample Date	17 Jul 2024	23 Mar 2024	---	---
Machine Hours	1948	1218	---	---
Oil Hours	0	0	---	---
Oil Changed	Changed	Not Chngd	---	---
Sample Status	ABNORMAL	ATTENTION	---	---

ALTA EQUIPMENT COMPANY
 5151 DR MARTIN LUTHER KING BLVD
 FORT MYERS, FL
 US 33905
 Contact: TODD LARK
 tlark@altaequipfl.com
 T:
 F: (239)481-3302



OIL CONDITION

Visc @ 40°C	cSt	█ 40.6	█ 41.4	---	---
Acid Number (AN)	mg KOH/g	█ 0.56	█ 0.52	---	---



CONTAMINATION

Water	%	NEG	NEG	---	---
Particles >4µm		▲ 17585	● 7302	---	---
Particles >6µm		█ 1277	█ 745	---	---
Particles >14µm		█ 28	█ 71	---	---
ISO 4406:1999 (c)		21/17/12	20/17/13	---	---
Silicon	ppm	█ 6	█ 3	---	---
Sodium	ppm	█ 2	█ 2	---	---
Potassium	ppm	█ 0	█ <1	---	---

Diagnosis

The filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition. All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.



WEAR METALS

Iron	ppm	█ 4	█ 2	---	---
Copper	ppm	█ 12	█ 7	---	---
Lead	ppm	█ 0	█ 0	---	---
Tin	ppm	█ 0	█ <1	---	---
Aluminum	ppm	█ 2	█ <1	---	---
Chromium	ppm	█ 0	█ 0	---	---
Molybdenum	ppm	█ 0	█ 0	---	---
Nickel	ppm	█ 0	█ 0	---	---
Titanium	ppm	0	0	---	---
Silver	ppm	0	0	---	---
Manganese	ppm	█ 0	█ 0	---	---
Vanadium	ppm	0	<1	---	---



ADDITIVES

Calcium	ppm	█ 96	█ 121	---	---
Magnesium	ppm	█ 1	█ 0	---	---
Zinc	ppm	█ 544	█ 548	---	---
Phosphorus	ppm	█ 425	█ 417	---	---
Barium	ppm	█ 0	█ 0	---	---
Boron	ppm	█ 0	█ 0	---	---

Depot: VOLVO0090
Unique No: 11130434
Signed: Wes Davis
Report Date: 22 Jul 2024




CONSTRUCTION EQUIPMENT




VOLVO GRAPHS

Ferrous Alloys




Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number

