



## WOODY SHUKOVSKY YANMAR M55546 - STARBOARD DIESEL ENGINE

Sample No: VPA050873

Oil Type: SHELL ROTELLA T 15W40

SAMPLE INFORMAT	TION			
Sample Number		VPA050873	 	
Sample Date		27 Oct 2023	 	
Machine Hours		925		
Oil Hours				
		0	 	
Oil Changed		Changed	 	
Sample Status		NORMAL	 	
OIL CONDITION				
Visc @ 100°C	cSt	<b>14.42</b>	 	
Base Number (BN)	mg KOH/g	<b>7.9</b>	 	
Oxidation (PA)	%	70	 	
CONTAMINATION				
	0.4			
Soot %	%	■0.2	 	
Nitration (PA)	%	63	 	
Sulfation (PA)	%	58	 	
Glycol	%	NEG	 	
Fuel	%	<b>0.6</b>	 	
Silicon	ppm	<b>■</b> 9	 	
Sodium	ppm	<b>2</b>	 	
Potassium	ppm	<b>7</b>	 	
WEAR METALS				
Iron	ppm	<b>□</b> 38	 	
Copper	ppm	<b>5</b>	 	
Lead	ppm	<b>■</b> <1	 	
Tin	ppm	0	 	
Aluminum		■3	 	
Chromium	ppm	<1	 	
Molybdenum		<b>■&lt;1</b>	 	
Nickel	ppm	_		
	ppm	<b>■</b> <1	 	
Titanium	ppm	<b>0</b>	 	
Silver	ppm	<b>■&lt;1</b>	 	
Manganese	ppm	<b></b>	 	
Vanadium	ppm	0	 	
ADDITIVES				
Calcium	ppm	<b>2167</b>	 	
Magnesium	ppm	<b>41</b>	 	
Zinc	ppm	<b>1277</b>	 	
Phosphorus	ppm	<b>1037</b>	 	
Barium	ppm	<b>0</b>	 	
Boron	ppm	<b>165</b>	 	
50.011	PPIII			

## **BEST MARINE**

24 RIVERVIEW AVE
TARRYTOWN, NY
US 10591
Contact: Service Manager
PETEMARINE27@OUTLOOK.COM
T: (516)807-5340
F:

## Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Depot:VPBESTARUnique No:10727896Signed:Doug BogartReport Date:14 Nov 2023

## **OIL ANALYSIS REPORT**



