



KOHLER SGM32FLG7 - PORT GENSET

Sample No: VPA060686

Oil Type: SHELL 15W40

| SAMPLE INFORMAT | TION | | | |
|------------------|-----------|----------------|------|--|
| | | | | |
| Sample Number | | VPA060686 | | |
| Sample Date | | 08 May 2024 | | |
| Machine Hours | | 1058 | | |
| Oil Hours | | 50 | | |
| Oil Changed | | Not Changd | | |
| Sample Status | | NORMAL | | |
| OIL CONDITION | | | | |
| Visc @ 100°C | cSt | □ 13.44 | | |
| Base Number (BN) | mg KOH/g | 9.5 | | |
| Oxidation (PA) | % | 80 | | |
| CONTAMINATION | | | | |
| CONTAMINATION | | | | |
| Water | % | NEG | | |
| Soot % | % | ■ 0.1 | | |
| Nitration (PA) | % | 47 | | |
| Sulfation (PA) | % | 59 | | |
| Glycol | % | NEG | | |
| Fuel | % | <1.0 | | |
| Silicon | ppm | ■ 9 | | |
| Sodium | ppm | 2 | | |
| Potassium | ppm | 2 | | |
| WEAR METALS | | | | |
| MEVII INFI VEZ | | | | |
| Iron | ppm | 4 | | |
| Copper | ppm | ■ <1 | | |
| Lead | ppm | 0 | | |
| Tin | ppm | ■ <1 | | |
| Aluminum | ppm | 2 | | |
| Chromium | ppm | ■<1 | | |
| Molybdenum | ppm | 40 | | |
| Nickel | ppm | ■0 | | |
| Titanium | ppm | <1 | | |
| Silver | ppm | ■ 0 | | |
| Manganese | ppm | ■0 | | |
| Vanadium | ppm | <1 | | |
| ADDITIVES | | | | |
| | 10.10.100 | - 172 <i>4</i> | | |
| Calcium | ppm | ■ 1724 | | |
| Magnesium | ppm | 472 | | |
| Zinc | ppm | ■ 932 | | |
| Phosphorus | ppm | ■806 | | |
| Barium | ppm | 0 | | |
| Boron | ppm | 79 | | |

SMART DIESEL SERVICE

102 NW 133RD AVE, UNIT 103 PLANTATION, FL US 33325 Contact: ANDRES GARMENDIA smartdieselservice@gmail.com T: (954)258-8100 F:

Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Depot:VPSMAPLAUnique No:11022090Signed:Doug BogartReport Date:10 May 2024

OIL ANALYSIS REPORT



