

OIL ANALYSIS REPORT

Area **CITY OF BRANDON HAMILTON GEAR #3 SCRAPER**

Component Gearbox Fluid

{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component.

Fluid Condition

The condition of the oil is acceptable for the time in service.




SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		LE0000308		
Sample Date		Client Info		26 Aug 2009		
Machine Age	mths	Client Info		360		
Oil Age	mths	Client Info		24		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		1		
Chromium	ppm	ASTM D5185(m)		<1		
Nickel	ppm	ASTM D5185(m)		0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)		0		
Lead	ppm	ASTM D5185(m)		<1		
Copper	ppm	ASTM D5185(m)		5		
Tin	ppm	ASTM D5185(m)		<1		
Vanadium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		9		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		<1		
Calcium	ppm	ASTM D5185(m)		3		
Phosphorus	ppm	ASTM D5185(m)		350		
Zinc	ppm	ASTM D5185(m)		2		
Sulfur	ppm	ASTM D5185(m)		1215		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		19		
Sodium	ppm	ASTM D5185(m)		0		
Potassium	ppm	ASTM D5185(m)		0		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	VLITE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*		NEG		
Free Water	scalar	Visual*		NEG		

Sample Rating Trend



OIL ANALYSIS REPORT



FLUID PROPERTIES	method	limit/base	current	history1	history
Visc @ 40°C cSt	ASTM D7279(m)		524		
SAMPLE IMAGES	method	limit/base	current	history1	history
Color				no image	no imag
Bottom				no image	no imag
GRAPHS					
Ferrous Alloys					
Non-ferrous Metals		Aug26/09			
Aug26/09		Aug26/09 -			
Viscosity @ 40°C		Aug26/09			
: 01557735 Tes	eived : 31	gton, ON L7L Aug 2009 Aug 2009	5H9 LUBRICA		OF CANADA STOL CIR DAKVILLE, CA 16H

Report Id: LUBOAK [WCAMIS] 01557735 (Generated: 04/24/2024 14:34:01) Rev: 1

CALA

ISO 17025:2017

Accredited Laboratory

Unique Number : 2964050

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

Test Package : IND 1

Diagnosed

:

Contact/Location: Dan Caruth - LUBOAK Page 2 of 2

CA L6H 5R3

Contact: Dan Caruth

danc@lubeng.com T: (905)829-3833

F: (905)829-2630