




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
FBDL
 Machine Id
HITACHI ZX245USLC-6 19HI70424
 Component
Reference New (Unused) Oil
 Fluid
PANOLIN HLP SYNTH E SPEC (240 LTR)

DIAGNOSIS

Recommendation

Il s'agit du relevé de base de l'échantillon soumis.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC	---	---
Sample Date	Client Info			12 Mar 2020	---	---
Machine Age	hrs Client Info			0	---	---
Oil Age	hrs Client Info			0	---	---
Oil Changed	Client Info			N/A	---	---
Sample Status				NORMAL	---	---

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method			NEG	---	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		0	---	---
Chromium	ppm	ASTM D5185(m)		0	---	---
Nickel	ppm	ASTM D5185(m)		0	---	---
Titanium	ppm	ASTM D5185(m)		<1	---	---
Silver	ppm	ASTM D5185(m)		<1	---	---
Aluminum	ppm	ASTM D5185(m)		1	---	---
Lead	ppm	ASTM D5185(m)		0	---	---
Copper	ppm	ASTM D5185(m)		0	---	---
Tin	ppm	ASTM D5185(m)		3	---	---
Antimony	ppm	ASTM D5185(m)		<1	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
Beryllium	ppm	ASTM D5185(m)		0	---	---
Cadmium	ppm	ASTM D5185(m)		0	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	2	---	---
Barium	ppm	ASTM D5185(m)	0	0	---	---
Molybdenum	ppm	ASTM D5185(m)	0	0	---	---
Manganese	ppm	ASTM D5185(m)	0	0	---	---
Magnesium	ppm	ASTM D5185(m)	0	0	---	---
Calcium	ppm	ASTM D5185(m)	0	1	---	---
Phosphorus	ppm	ASTM D5185(m)	190	193	---	---
Zinc	ppm	ASTM D5185(m)	0	<1	---	---
Sulfur	ppm	ASTM D5185(m)	1750	2014	---	---
Lithium	ppm	ASTM D5185(m)		<1	---	---



CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		<1	---	---
Sodium	ppm	ASTM D5185(m)		0	---	---
Potassium	ppm	ASTM D5185(m)	>20	<1	---	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*		0	---	---
Nitration	Abs/cm	ASTM D7624*		2.4	---	---
Sulfation	Abs.1mm	ASTM D7415*		32.0	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs.1mm	ASTM D7414*		27.3	---	---





OIL ANALYSIS REPORT




VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---
Precipitate	scalar	Visual*	NONE	NONE	---	---
Silt	scalar	Visual*	NONE	NONE	---	---
Debris	scalar	Visual*	NONE	NONE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D7279(m)	46.5	46.7	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	8.6	8.5	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	165	160	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC **Received** : 16 Mar 2020
Lab Number : **02343933** **Tested** : 20 Mar 2020
Unique Number : 5019361 **Diagnosed** : 20 Mar 2020 - Bill Quesnel
Test Package : TEST (Additional Tests: FT-IR, ICP, KV100, KV40, VI)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Envirolin Canada
 520 rue Adanac
 Quebec, QC
 CA G1C 7B7
 Contact: Patrick Levesque
 patrick.levesque@envirolin.com
 T: (418)623-1216
 F: (418)660-8889