


# **OIL ANALYSIS REPORT**

# WEST BOP CRANE **Q-1705A WEST MAIN HOIST**

Component Gearbox

GEAR OIL SAE 75W90 (--- GAL)



#### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the


#### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

| OAMBLE INCOR     | AATION   |               | 11 11 11   | Jul2022     | 111      |          |
|------------------|----------|---------------|------------|-------------|----------|----------|
| SAMPLE INFORM    | MATION   | method        | limit/base | current     | history1 | history2 |
| Sample Number    |          | Client Info   |            | WC0724467   |          |          |
| Sample Date      |          | Client Info   |            | 16 Jul 2022 |          |          |
| Machine Age      | yrs      | Client Info   |            | 0           |          |          |
| Oil Age          | yrs      | Client Info   |            | 0           |          |          |
| Oil Changed      |          | Client Info   |            | Not Changd  |          |          |
| Sample Status    |          |               |            | NORMAL      |          |          |
| CONTAMINATIO     | N        | method        | limit/base | current     | history1 | history2 |
| Water            |          | WC Method     | >0.2       | NEG         |          |          |
| WEAR METALS      |          | method        | limit/base | current     | history1 | history2 |
| PQ               |          | ASTM D8184*   |            | 3           |          |          |
| Iron             | ppm      | ASTM D5185(m) | >200       | 11          |          |          |
| Chromium         | ppm      | ASTM D5185(m) | >15        | 0           |          |          |
| Nickel           | ppm      | ASTM D5185(m) | >15        | 0           |          |          |
| Titanium         | ppm      | ASTM D5185(m) |            | 0           |          |          |
| Silver           | ppm      | ASTM D5185(m) |            | 0           |          |          |
| Aluminum         | ppm      | ASTM D5185(m) | >25        | <1          |          |          |
| Lead             | ppm      | ASTM D5185(m) | >100       | 2           |          |          |
| Copper           | ppm      | ASTM D5185(m) | >200       | 7           |          |          |
| Tin              | ppm      | ASTM D5185(m) | >25        | <1          |          |          |
| Antimony         | ppm      | ASTM D5185(m) |            | 3           |          |          |
| Vanadium         | ppm      | ASTM D5185(m) |            | 0           |          |          |
| Beryllium        | ppm      | ASTM D5185(m) |            | 0           |          |          |
| Cadmium          | ppm      | ASTM D5185(m) |            | 0           |          |          |
| ADDITIVES        |          | method        | limit/base | current     | history1 | history2 |
| Boron            | ppm      | ASTM D5185(m) | 400        | 142         |          |          |
| Barium           | ppm      | ASTM D5185(m) | 200        | 0           |          |          |
| Molybdenum       | ppm      | ASTM D5185(m) | 12         | <1          |          |          |
| Manganese        | ppm      | ASTM D5185(m) |            | <1          |          |          |
| Magnesium        | ppm      | ASTM D5185(m) | 12         | <1          |          |          |
| Calcium          | ppm      | ASTM D5185(m) | 150        | 17          |          |          |
| Phosphorus       | ppm      | ASTM D5185(m) | 1650       | 1020        |          |          |
| Zinc             | ppm      | ASTM D5185(m) | 125        | 8           |          |          |
| Sulfur           | ppm      | ASTM D5185(m) | 22500      | 22237       |          |          |
| Lithium          | ppm      | ASTM D5185(m) |            | <1          |          |          |
| CONTAMINANTS     | ;        | method        | limit/base | current     | history1 | history2 |
| Silicon          | ppm      | ASTM D5185(m) | >50        | <1          |          |          |
| Sodium           | ppm      | ASTM D5185(m) |            | 2           |          |          |
| Potassium        | ppm      | ASTM D5185(m) | >20        | 2           |          |          |
| FLUID DEGRADA    | ATION _  | method        | limit/base | current     | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D974*    | 2.00       | 3.12        |          |          |



## **OIL ANALYSIS REPORT**





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number **Unique Number** 

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9

: WC0724467

: 02505345 : 5438306

Recieved Diagnosed Diagnostician

: 15 Aug 2022 : 16 Aug 2022 : Kevin Marson Test Package : IND 2 (Additional Tests: TAN Man)

**Parker Wellbore** 215 Water Street, Suite 802, PO Box 74 St. John's, NL CA A1C 6C9

Contact: HMDC Material Control Coordinator hmdc.material.control.coordinator@exxonmobil.com T:

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

F: