



PROBLEM SUMMARY

Sample Rating Trend

WEAR



Machine Id
L43 VALVE 2 RETRACT


Component
Hydraulic System

Fluid
NOT GIVEN (--- GAL)



May2023

COMPONENT CONDITION SUMMARY



RECOMMENDATION

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. Check seals and/or filters for points of contaminant entry. We advise that you check all areas where contaminants can enter the system. The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather. We advise that you use off-line filtration with water adsorbent filters to attempt to remove the water from this oil. We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid. Resample in 30-45 days to monitor this situation. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample. Please provide more complete information on your next sample.

PROBLEMATIC TEST RESULTS

Sample Status				SEVERE	---	---
Iron	ppm	ASTM D5185(m)	>20	224	---	---
Silicon	ppm	ASTM D5185(m)	>15	21	---	---
Water	%	ASTM D6304*	>0.05	0.060	---	---
ppm Water	ppm	ASTM D6304*	>500	603.5	---	---
Particles >4µm		ASTM D7647	>5000	81295	---	---
Particles >6µm		ASTM D7647	>1300	32693	---	---
Particles >14µm		ASTM D7647	>160	4495	---	---
Particles >21µm		ASTM D7647	>40	1327	---	---
Particles >38µm		ASTM D7647	>10	66	---	---
Oil Cleanliness		ISO 4406 (c)	>19/17/14	24/22/19	---	---
Acid Number (AN)	mg KOH/g	ASTM D974*		5.09	---	---

Customer Id: FORHAM
 Sample No.: PP
 Lab Number: 02564376
 Test Package: IND 3



To manage this report scan the QR code

To discuss the diagnosis or test data:
 Kevin Marson +1 (289)291-4644 x4644
Kevin.Marson@wearcheck.com

To change component or sample information:
 Gloria Gonzalez +1 (289)291-4643 x4643
gloria.gonzalez@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Filter	---	---	?	We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid.
Resample	---	---	?	Resample in 30-45 days to monitor this situation.
Alert	---	---	?	Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment.
Information Required	---	---	?	Please specify the brand, type, and viscosity of the oil on your next sample. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please provide more complete information on your next sample.
Check Breathers	---	---	?	The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather.
Check Dirt Access	---	---	?	We advise that you check all areas where contaminants can enter the system.
Check Seals	---	---	?	Check seals and/or filters for points of contaminant entry.
Filter Fluid	---	---	?	We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid.

HISTORICAL DIAGNOSIS




OIL ANALYSIS REPORT

Sample Rating Trend

WEAR



Machine Id
L43 VALVE 2 RETRACT
 Component
Hydraulic System
 Fluid
NOT GIVEN (--- GAL)



DIAGNOSIS

Recommendation

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. Check seals and/or filters for points of contaminant entry. We advise that you check all areas where contaminants can enter the system. The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather. We advise that you use off-line filtration with water adsorbent filters to attempt to remove the water from this oil. We advise that you perform a filter service, and use off-line filtration to improve the cleanliness of the system fluid. Resample in 30-45 days to monitor this situation. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample. Please provide more complete information on your next sample.

Wear

Iron ppm levels are severe. The low ferrous density (PQ) index indicates the wear metal levels are due to corrosion. The direct-reading & analytical ferrographic results are normal indicating no abnormal wear in the system.

Contaminants

There is a high amount of particulates (2 to 100 microns in size) present in the oil. There is a moderate concentration of water present in the oil. There is a moderate concentration of dirt present in the oil. High amount of ingressed dirt has caused abrasive wear to the component.

Oil Condition

The AN level is above the recommended limit. The oil is no longer serviceable as a result of the abnormal and/or severe wear.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PP	---	---
Sample Date	Client Info		11 May 2023	---	---
Machine Age	hrs	Client Info	0	---	---
Oil Age	hrs	Client Info	0	---	---
Oil Changed	Client Info		N/A	---	---
Sample Status			SEVERE	---	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		0	---	---
Iron	ppm	ASTM D5185(m) >20	224	---	---
Chromium	ppm	ASTM D5185(m) >20	2	---	---
Nickel	ppm	ASTM D5185(m) >20	<1	---	---
Titanium	ppm	ASTM D5185(m)	0	---	---
Silver	ppm	ASTM D5185(m)	0	---	---
Aluminum	ppm	ASTM D5185(m) >20	<1	---	---
Lead	ppm	ASTM D5185(m) >20	2	---	---
Copper	ppm	ASTM D5185(m) >20	3	---	---
Tin	ppm	ASTM D5185(m) >20	0	---	---
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	2	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	<1	---	---
Barium	ppm	ASTM D5185(m)	<1	---	---
Molybdenum	ppm	ASTM D5185(m)	0	---	---
Manganese	ppm	ASTM D5185(m)	3	---	---
Magnesium	ppm	ASTM D5185(m)	56	---	---
Calcium	ppm	ASTM D5185(m)	155	---	---
Phosphorus	ppm	ASTM D5185(m)	287	---	---
Zinc	ppm	ASTM D5185(m)	48	---	---
Sulfur	ppm	ASTM D5185(m)	5957	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---





CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >15	21	---	---
Sodium	ppm	ASTM D5185(m)	3	---	---
Potassium	ppm	ASTM D5185(m) >20	35	---	---
Water	%	ASTM D6304* >0.05	0.060	---	---
ppm Water	ppm	ASTM D6304* >500	603.5	---	---

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	81295	---	---
Particles >6µm	ASTM D7647	>1300	32693	---	---
Particles >14µm	ASTM D7647	>160	4495	---	---
Particles >21µm	ASTM D7647	>40	1327	---	---
Particles >38µm	ASTM D7647	>10	66	---	---
Particles >71µm	ASTM D7647	>3	5	---	---
Oil Cleanliness	ISO 4406 (c)	>19/17/14	24/22/19	---	---

OIL ANALYSIS REPORT








FLUID DEGRADATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	▲ 5.09	---	---

VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	---
Emulsified Water	scalar	Visual*	>0.05	NEG	---
Free Water	scalar	Visual*		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	▲ 782	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PP **Received** : 15 Jun 2023
Lab Number : 02564376 **Diagnosed** : 21 Jun 2023
Unique Number : 5593417 **Diagnostician** : Kevin Marson
Test Package : IND 3 (Additional Tests: KF, TAN Man)

FORSYTHE LUBRICATION
 120 CHATHAM ST.
 HAMILTON, ON
 CA L8P 2B5
 Contact: HEIDI LEINGARTNER


To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T: (905)525-7192
 F: (905)525-7024

FERROGRAPHY REPORT

Machine Id
L43 VALVE 2 RETRACT
 Component
Hydraulic System
 Fluid
NOT GIVEN (--- GAL)


Magn: 200x Illum: BC



Magn: 50x Illum: RW



Magn: 100x Illum: RW




DR-FERROGRAPHY		method	limit/base	current	history1	history2
Large Particles		DR-Ferr*		57.3	---	---
Small Particles		DR-Ferr*		11.7	---	---
Total Particles		DR-Ferr*	>---	69	---	---
Large Particles Percentage	%	DR-Ferr*		66.1	---	---
Severity Index		DR-Ferr*		2613	---	---

FERROGRAPHY		method	limit/base	current	history1	history2
Ferrous Rubbing	Scale 0-10	ASTM D7684*		<div style="width: 30px; height: 10px; background-color: #28a745;"></div> 3		
Ferrous Sliding	Scale 0-10	ASTM D7684*				
Ferrous Cutting	Scale 0-10	ASTM D7684*				
Ferrous Rolling	Scale 0-10	ASTM D7684*		<div style="width: 10px; height: 10px; background-color: #28a745;"></div> 1		
Ferrous Break-in	Scale 0-10	ASTM D7684*				
Ferrous Spheres	Scale 0-10	ASTM D7684*				
Ferrous Black Oxides	Scale 0-10	ASTM D7684*				
Ferrous Red Oxides	Scale 0-10	ASTM D7684*				
Ferrous Corrosive	Scale 0-10	ASTM D7684*				
Ferrous Other	Scale 0-10	ASTM D7684*				
Nonferrous Rubbing	Scale 0-10	ASTM D7684*				
Nonferrous Sliding	Scale 0-10	ASTM D7684*				
Nonferrous Cutting	Scale 0-10	ASTM D7684*				
Nonferrous Rolling	Scale 0-10	ASTM D7684*				
Nonferrous Other	Scale 0-10	ASTM D7684*				
Carbonaceous Material	Scale 0-10	ASTM D7684*				
Lubricant Degradation	Scale 0-10	ASTM D7684*				
Sand/Dirt	Scale 0-10	ASTM D7684*		<div style="width: 10px; height: 10px; background-color: #28a745;"></div> 1		
Fibres	Scale 0-10	ASTM D7684*				
Spheres	Scale 0-10	ASTM D7684*				
Other	Scale 0-10	ASTM D7684*		<div style="width: 10px; height: 10px; background-color: #28a745;"></div> 1		

WEAR

Iron ppm levels are severe. The low ferrous density (PQ) index indicates the wear metal levels are due to corrosion. The direct-reading & analytical ferrographic results are normal indicating no abnormal wear in the system.



This page left intentionally blank