




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**PUMPHOUSE/HOOD COOLING PUMPS**  
 Machine Id  
**C - Hood Cooling 2 Electric Pump OB**

Component  
**Lube System**

Fluid  
**PETRO CANADA HYDREX AW 100 (1 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0850128</b>	WC0824414	WC0785676
Sample Date	Client Info		<b>16 Aug 2023</b>	31 May 2023	27 Jan 2023
Machine Age	hrs	Client Info	<b>0</b>	0	0
Oil Age	hrs	Client Info	<b>0</b>	0	0
Oil Changed	Client Info		<b>N/A</b>	N/A	N/A
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*	>DFLT	<b>0</b>	0	0
Iron	ppm	ASTM D5185(m) >20	<b>2</b>	3	1
Chromium	ppm	ASTM D5185(m) >20	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m) >20	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)	<b>&lt;1</b>	0	0
Aluminum	ppm	ASTM D5185(m) >20	<b>&lt;1</b>	0	<1
Lead	ppm	ASTM D5185(m) >20	<b>0</b>	0	0
Copper	ppm	ASTM D5185(m) >20	<b>&lt;1</b>	<1	<1
Tin	ppm	ASTM D5185(m) >20	<b>0</b>	0	0
Antimony	ppm	ASTM D5185(m)	<b>0</b>	0	<1
Vanadium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Beryllium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185(m)	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	<1	3
Barium	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	<1	<1
Molybdenum	ppm	ASTM D5185(m) 0	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m) 0	<b>0</b>	0	0
Magnesium	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	0	<1
Calcium	ppm	ASTM D5185(m) 50	<b>50</b>	50	46
Phosphorus	ppm	ASTM D5185(m) 330	<b>354</b>	356	362
Zinc	ppm	ASTM D5185(m) 430	<b>424</b>	397	364
Sulfur	ppm	ASTM D5185(m) 760	<b>2505</b>	2575	3121
Lithium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	<1

## CONTAMINANTS






	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >15	<b>3</b>	3	2
Sodium	ppm	ASTM D5185(m)	<b>&lt;1</b>	0	<1
Potassium	ppm	ASTM D5185(m) >20	<b>0</b>	0	0

## FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		<b>10310</b>	8985	6970
Particles >6µm	ASTM D7647	>10240000	<b>1642</b>	1068	1068
Particles >14µm	ASTM D7647	>10240000	<b>102</b>	31	56
Particles >21µm	ASTM D7647	>25600000	<b>32</b>	9	14
Particles >38µm	ASTM D7647	>640000	<b>2</b>	0	0
Particles >71µm	ASTM D7647	>160000	<b>1</b>	0	0
Oil Cleanliness	ISO 4406 (c)	>--/30/30	<b>21/18/14</b>	20/17/12	20/17/13



# OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.60	<b>0.61</b>	0.43	0.58






VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Precipitate	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Silt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	Visual*	NONE	<b>VLITE</b>	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>5	<b>NEG</b>	NEG	NEG
Free Water	scalar	Visual*		<b>NEG</b>	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	101	<b>96.5</b>	106	110

SAMPLE IMAGES		method	limit/base	current	history1	history2
---------------	--	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **STELCO - BOSC - Basic Oxygen Slab Caster**  
**Sample No.** : WC0850128 **Received** : 16 Aug 2023 2330 Regional Road #3, Door: BOSC8  
**Lab Number** : 02576247 **Diagnosed** : 16 Aug 2023 NANTICOKE, ON  
**Unique Number** : 5629307 **Diagnostician** : Wes Davis CA N0A 1L0  
**Test Package** : IND 2 ( Additional Tests: PQ, TAN Man )  
 Contact: Tom Walden  
 Thomas.Walden@stelco.com  
 T: (519)587-4541  
 F: (519)587-7702

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.