




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Clandonald station
 Machine Id
MP-01 CLAF LUBE SKID
 Component
Lube System
 Fluid
ROYAL PURPLE SYNFILM GT 46 (205 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0805003	WC0729591	WC0729599
Sample Date	Client Info		11 Aug 2023	01 Mar 2023	14 Sep 2022
Machine Age	hrs	Client Info	46500	42500	0
Oil Age	hrs	Client Info	46500	42500	38500
Oil Changed	Client Info		N/A	N/A	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>20	<1	<1	<1
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>20	0	0	<1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)		0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	<1	<1	0
Lead	ppm	ASTM D5185(m)	>20	0	<1	0
Copper	ppm	ASTM D5185(m)	>20	4	4	4
Tin	ppm	ASTM D5185(m)	>20	0	0	0
Antimony	ppm	ASTM D5185(m)		0	0	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	0	<1	<1	0
Barium	ppm	ASTM D5185(m)	0	0	0	0
Molybdenum	ppm	ASTM D5185(m)	0	0	0	0
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)	95	78	80	79
Calcium	ppm	ASTM D5185(m)	0	2	0	1
Phosphorus	ppm	ASTM D5185(m)	0	75	77	77
Zinc	ppm	ASTM D5185(m)	0	3	1	2
Sulfur	ppm	ASTM D5185(m)	15000	14976	14866	14925
Lithium	ppm	ASTM D5185(m)		<1	<1	<1

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>15	<1	<1	1
Sodium	ppm	ASTM D5185(m)		1	<1	<1
Potassium	ppm	ASTM D5185(m)	>20	1	0	0

FLUID CLEANLINESS





	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	257	214	261
Particles >6µm	ASTM D7647	>1300	84	79	64
Particles >14µm	ASTM D7647	>160	11	5	7
Particles >21µm	ASTM D7647	>40	4	1	2
Particles >38µm	ASTM D7647	>10	0	1	1
Particles >71µm	ASTM D7647	>3	0	0	1
Oil Cleanliness	ISO 4406 (c)	>19/17/14	15/14/11	15/13/10	15/13/10

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.49	0.36	0.53



OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.05	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	46.0	42.7	42.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0805003 **Received** : 17 Aug 2023
Lab Number : 02576430 **Diagnosed** : 18 Aug 2023
Unique Number : 5629490 **Diagnostician** : Wes Davis
Test Package : IND 2 (Additional Tests: TAN MAN)

INTER PIPELINE LTD.
 BOX 540
 HARDISTY, AB
 CA T0B 1V0
 Contact: Austin Wilson
 Austin.wilson@interpipeline.com
 T: (825)997-4799
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.