


## **FUEL REPORT**

Area [44096] VR7000063

Component **Diesel Fuel** 






No.2 DIESEL FUEL (ULTRALOW SULPHU	R) ( GAL)				Aug2023		
DIAGNOSIS	SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		KT0000110		
Laboratory test indicate that this fuel is suitable for	Sample Date		Client Info		14 Aug 2023		
use and meets all test requirements. Resample at	Machine Age	hrs	Client Info		0		
the next service interval to monitor.	Sample Status				NORMAL		
Corrosion {not applicable}	PHYSICAL PROP	ERTIES	method	limit/base	current	history1	history2
Contaminants The system cleanliness is acceptable for your target	Specific Gravity		ASTM D1298*	0.839	0.835		
	Fuel Color	text	Visual Screen*	Yllow	Yllow		
ISO 4406 cleanliness code. The water content is	Visc @ 40°C	cSt	ASTM D7279(m)	3.0	2.4		
negligible. There is no indication of any contamination in the diesel fuel.	Pensky-Martens Flash Point	°C	ASTM D7215*	52	50.4		
Fuel Condition  All laboratory tests indicate that this sample meets specifications for No.2 ultra-low-sulfur diesel fuel	SULFUR CONTE	NT	method				history2
	Sulfur	ppm	ASTM D5185(m)	10	11		
(US EPA/CGSB-3.517-3 type B).	DISTILLATION		method				history2
	Lateral Darling Darling		4 OT1 4 D 00007*	405	450		

Specific Gravity		ASTM D1298*	0.839	0.835		
Fuel Color	text	Visual Screen*	Yllow	Yllow		
/isc @ 40°C	cSt	ASTM D7279(m)	3.0	2.4		
Pensky-Martens Flash Point	°C	ASTM D7215*	52	50.4		
SULFUR CONTE	NT	method	limit/base	current	history1	history2
Sulfur	ppm	ASTM D5185(m)	10	11		
DISTILLATION		method	limit/base	current	history1	history2
Initial Boiling Point	°C	ASTM D2887*	165	159		
5% Distillation Point	°C	ASTM D2887*		180		
10% Distill Point	°C	ASTM D2887*	201	192		
15% Distillation Point	°C	ASTM D2887*		201		
20% Distill Point	°C	ASTM D2887*	216	209		
30% Distill Point	°C	ASTM D2887*	230	226		
40% Distill Point	°C	ASTM D2887*	243	241		
50% Distill Point	°C	ASTM D2887*	255	257		
60% Distill Point	°C	ASTM D2887*	267	272		
70% Distill Point	°C	ASTM D2887*	280	287		
80% Distill Point	°C	ASTM D2887*	295	303		
85% Distillation Point	°C	ASTM D2887*		314		
90% Distill Point	°C	ASTM D2887*	310	325		
95% Distillation Point	°C	ASTM D2887*		345		
Final Boiling Point	°C	ASTM D2887*	341	362		
IGNITION QUALIT	ΓΥ	method	limit/base	current	history1	history2
API Gravity		ASTM D1298*	37.7	37		
Cetane Index		ASTM D4737*	<40.0	49		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	<1.0	0		
Sodium	ppm	ASTM D5185(m)	< 0.1	<1		
Potassium	ppm	ASTM D5185(m)	<0.1	0		
Water	%	ASTM D6304*	< 0.05	0.003		
ppm Water	ppm	ASTM D6304*	<500	29.9		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>2500	237		
Particles >6µm		ASTM D7647	>640	70		
Particles >14µm		ASTM D7647	>80	11		
Particles >21µm		ASTM D7647		5		
Davida a 00		AOTM DZ04Z	4	•		



## **FUEL REPORT**



Validity of results and interpretation are based on the sample and information as supplied.