


Chem-Ecol

A2308078

OIL ANALYSIS REPORT

Sample Rating Trend







Component Unknown Component Fluid CHEM-ECOL FORMING OIL 185 (--- GAL)

DIAGNOSIS

Recommendation

This is a baseline read-out on the submitted sample.

Wear

{not applicable}


Contamination {not applicable}

Fluid Condition {not applicable}


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		E30000104		
Sample Date		Client Info		17 Aug 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		<1		
Chromium	ppm	ASTM D5185(m)		0		
Nickel	ppm	ASTM D5185(m)		<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		<1		
Aluminum	ppm	ASTM D5185(m)		0		
Lead	ppm	ASTM D5185(m)		0		
Copper	ppm	ASTM D5185(m)		2		
Tin	ppm	ASTM D5185(m)		0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		78		
Calcium	ppm	ASTM D5185(m)		64		
Phosphorus	ppm	ASTM D5185(m)		238		
Zinc	ppm	ASTM D5185(m)		294		
Sulfur	ppm	ASTM D5185(m)		701		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		1		
Sodium	ppm	ASTM D5185(m)		2		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water	%	ASTM D6304*		0.002		
ppm Water	ppm	ASTM D6304*		21.8		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	440		
Particles >6µm		ASTM D7647	>1300	156		
Particles >14µm		ASTM D7647	>160	19		
Particles >21µm		ASTM D7647	>40	7		
Particles >38µm		ASTM D7647	>10	2		
Particles >71µm		ASTM D7647	>3	2		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	16/14/11		
2:17:04) Rev: 1				a	ion: Tatiana Soi	



OIL ANALYSIS REPORT







FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.38		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate Silt	scalar scalar	Visual* Visual*	NONE	NONE NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor Emulsified Water	scalar scalar	Visual* Visual*	NORML	NORML NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D7279(m)	185	194		
/isc @ 100°C	cSt	ASTM D7279(m)		18.1		
Viscosity Index (VI)	Scale	ASTM D2270*		102		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					no image	no image
Bottom				C	no image	no image
GRAPHS			_			5
Ferrous Alloys			491,520	Particle Count		т26
iron chromium			122,880			-24
nickel			30,720	Severe		-22
L. 			EZ (1 7,680	Abnormal		-20
Aug17/23			Aug 17/23 1/20 1/20 1/20 480 480		÷	-20 -18 -16
Non-ferrous Metals	5		480 bartick	~ ``		-16
copper			120 			-14
tin tin						-12 8
53			8 23			
Aug17/23			Aug17/23			-8
Viscosity @ 40°C			4	ونام مرافع Acid Number	14μ 21μ	38µ 71µ
Abnormal			04.0 40 05.0 Mumber (mg KOH(g)			
Base			<u>ل</u> في 0.20			
			P 0.00			
Abnormal				~		
Annormal 2011/23			Aug17/23 -	Aug17/23		Aug17/23

: 28 Aug 2023

Diagnostician : Tatiana Sorkina

Diagnosed

Test Package : IND 2 (Additional Tests: KF, KV100, PrtCount, VI)

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

To discuss this sample report, contact Customer Service at 1-800-268-2131.

640 Victoria Street Cobourg, ON CA K9A 5H5 Contact: Tatiana Sorkina tsorkina@e360s.ca T: (800)263-3939 F: (905)373-4950