


# NOR BULK

Component New (Unused) Oil Fluid CHEVRON 1000 THF (780 LTR)

#### COMPONENT CONDITION SUMMARY



#### RECOMMENDATION

This is the baseline readout on this new (unused) oil. The fluid is suitable for service. We recommend an early resample to monitor this condition. NOTE: New oils are not generally filtered or guaranteed to a certain cleanliness code. We advise that you verify the target cleanliness code for your application and recommend the use of a portable filter cart to fill any system with a target code below the ISO cleanliness code of this product.

#### **PROBLEMATIC TEST RESULTS**

Sample Status			ABNORMAL	 
Particles >4µm	ASTM D7647	>5000	🔺 12659	 
Particles >6µm	ASTM D7647	>1300	<b>4296</b>	 
Particles >14µm	ASTM D7647	>160	<u> </u>	 
Particles >21µm	ASTM D7647	>40	<u> </u>	 
Oil Cleanliness	ISO 4406 (c)	>19/17/14	<u> </u>	 


Customer Id: SAL364SAL Sample No.: WC0815332 Lab Number: 02579101 Test Package: IND 2



To manage this report scan the QR code

*To discuss the diagnosis or test data:* Kevin Marson +1 (289)291-4644 x4644 Kevin.Marson@wearcheck.com

*To change component or sample information:* Gloria Gonzalez +1 (289)291-4643 x4643 <u>gloria.gonzalez@wearcheck.com</u>



RECOMMENDED ACTIONS						
Action	Status	Date	Done By	Description		
Resample			?	We recommend an early resample to monitor this condition.		
Alert			?	NOTE: New oils are not generally filtered or guaranteed to a certain cleanliness code. We advise that you verify the target cleanliness code for your application and recommend the use of a portable filter cart to fill any system with a target code below the ISO cleanliness code of this product.		

HISTORICAL DIAGNOSIS



### **OIL ANALYSIS REPORT**

Sample Rating Trend

ISO

#### Machine Id NOR BULK Component New (Unused) Oil Fluid

CHEVRON 1000 THF (780 LTR)

#### DIAGNOSIS

#### Recommendation

This is the baseline readout on this new (unused) oil. The fluid is suitable for service. We recommend an early resample to monitor this condition. NOTE: New oils are not generally filtered or guaranteed to a certain cleanliness code. We advise that you verify the target cleanliness code for your application and recommend the use of a portable filter cart to fill any system with a target code below the ISO cleanliness code of this product.

#### Wear

{not applicable}

#### Contamination

There is a moderate amount of particulates (2 to 100 microns in size) present in the oil.


#### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for service. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0815332		
Sample Date		Client Info		20 Jul 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				ABNORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		<1		
Chromium	ppm	ASTM D5185(m)		0		
Nickel	ppm	ASTM D5185(m)		<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)		<1		
Lead	ppm	ASTM D5185(m)		0		
Copper	ppm	ASTM D5185(m)		<1		
Tin	ppm	ASTM D5185(m)		0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		12		
	ppm	( )				
Barium	ppm	ASTM D5185(m)		0		
Barium Molybdenum		. ,		0 4		
	ppm	ASTM D5185(m)				
Molybdenum	ppm ppm	ASTM D5185(m) ASTM D5185(m)		4		
Molybdenum Manganese	ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0		
Molybdenum Manganese Magnesium	ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23		
Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23 2640		 
Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23 2640 985		
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23 2640 985 1162	  	
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	limit/base	4 0 23 2640 985 1162 2781	   	   
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	limit/base	4 0 23 2640 985 1162 2781 <1		
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium CONTAMINANTS	ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)	limit/base	4 0 23 2640 985 1162 2781 <1 <1		
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium CONTAMINANTS Silicon	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23 2640 985 1162 2781 <1 <1 current 17		
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium CONTAMINANTS Silicon Sodium	ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m) ASTM D5185(m)		4 0 23 2640 985 1162 2781 <1 <1	     history1	     history2
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium CONTAMINANTS Silicon Sodium Potassium	ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m)	>20	4 0 23 2640 985 1162 2781 <1 current 17 <1 0	     history1  	     history2
Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur Lithium CONTAMINANTS Silicon Sodium Potassium INFRA-RED	ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185(m) ASTM D5185(m)	>20	4 0 23 2640 985 1162 2781 <1 2781 <1 <1 17 <1 0 0 current	     history1   history1	     history2    history2



## **OIL ANALYSIS REPORT**







FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	<b>12659</b>		
Particles >6µm		ASTM D7647	>1300	<b>4296</b>		
Particles >14µm		ASTM D7647	>160	<b>4</b> 61		
Particles >21µm		ASTM D7647	>40	<u> </u>		
Particles >38µm		ASTM D7647	>10	3		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	<b>4</b> 21/19/16		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*		8.6		
Acid Number (AN)	mg KOH/g	ASTM D974*		2.34		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	VLITE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*		NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	58.4	58.7		
Visc @ 100°C	cSt	ASTM D7279(m)	9.5	9.4		
Viscosity Index (VI)	Scale	ASTM D2270*	145	141		
SAMPLE IMAGES	2	method	limit/base	current	history1	history2



: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Salford Group Inc Laboratory CALA 同條 Sample No. : WC0815332 Received : 29 Aug 2023 364018 McBeth Rd Lab Number : 02579101 Diagnosed : 30 Aug 2023 Salford, ON ISO 17025:2017 Accredited Laboratory Unique Number : 5632161 Diagnostician : Kevin Marson CA N0J 1W0 Test Package : IND 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, TAN MAN, VI) Contact: Chris Poppe To discuss this sample report, contact Customer Service at 1-800-268-2131. chris.poppe@salfordgroup.com T: (519)485-3977 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied. F: