

OIL ANALYSIS REPORT

(C-GFCU)
Machine Id
[C-GFCU] CESSNA L-21806-27A

Piston Aircraft Engine

SHELL AEROSHELL W 15W50 MGR (8 LTR)

Sample Rating Trend



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

R)			May2023	Jul2023		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0834779	WC0740390	
Sample Date		Client Info		24 Jul 2023	18 May 2023	
TSN	hrs	Client Info		2993	2993	
TSO	hrs	Client Info		880	0	
Oil Age	hrs	Client Info		50	50	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	٧	method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	<1.0	<1.0	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>90	25	26	
Chromium	ppm	ASTM D5185(m)	>20	6	8	
Nickel	ppm	ASTM D5185(m)	>15	3	3	
Titanium	ppm	ASTM D5185(m)		0	0	
Silver	ppm	ASTM D5185(m)	>5	0	0	
Aluminum	ppm	ASTM D5185(m)	>25	9	14	
Lead	ppm	ASTM D5185(m)	>20000	4083	2000	
Copper	ppm	ASTM D5185(m)	>25	19	9	
Tin	ppm	ASTM D5185(m)	>30	0	<1	
Antimony	ppm	ASTM D5185(m)		0	0	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		1	1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1	<1	
Barium	ppm	ASTM D5185(m)		0	0	
Molybdenum	ppm	ASTM D5185(m)	5	0	0	
Manganese	ppm	ASTM D5185(m)		0	0	
Magnesium	ppm	ASTM D5185(m)	10	<1	<1	
Calcium	ppm	ASTM D5185(m)	10	1	2	
Phosphorus	ppm	ASTM D5185(m)	1280	1107	1238	
Zinc	ppm	ASTM D5185(m)	10	10	6	
Sulfur	ppm	ASTM D5185(m)	1800	2670	2306	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	3	5	
Sodium	ppm	ASTM D5185(m)		<1	<1	
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	





OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
Precipitate	scalar	Visual*	NONE	NONE	NONE	
Silt	scalar	Visual*	NONE	LIGHT	LIGHT	
Debris	scalar	Visual*	NONE	NONE	NONE	
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
Appearance	scalar	Visual*	NORML	NORML	NORML	
Odor	scalar	Visual*	NORML	NORML	NORML	
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	
Free Water	scalar	Visual*		NEG	NEG	

FLUID PROPERTIES		method				history2
Visc @ 100°C	cSt	ASTM D7279(m)	18.2	21.0	19.9	









CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number Unique Number : 5632386 Test Package : AVI 1

: 02579326

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : WC0834779 Received

Diagnosed

: 30 Aug 2023 : 30 Aug 2023

Diagnostician : Kevin Marson

2833 - 16TH AVENUE,, HANGAR 9 MARKHAM, ON CA L3R 0P8

Contact: Joanne joanne.airpartners@gmail.com

AIR PARTNERS INC.

F: (905)513-8986

Contact/Location: Joanne ? - AIRMAR

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.