




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
NOVA BUS EQ60067

Component
Rear Diesel Engine

Fluid
VALVOLINE 15W40 (24 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC0809092	WC0770735	WC0770705
Sample Date	Client Info			28 Aug 2023	01 May 2023	10 Jan 2023
Machine Age	kms	Client Info		481821	459395	437145
Oil Age	kms	Client Info		10000	10000	10000
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method		>3.0	<1.0	<1.0	<1.0
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>90	13	12	13
Chromium	ppm	ASTM D5185(m)	>20	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>2	0	<1	0
Titanium	ppm	ASTM D5185(m)	>2	0	<1	0
Silver	ppm	ASTM D5185(m)	>2	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	1	2	2
Lead	ppm	ASTM D5185(m)	>40	<1	0	<1
Copper	ppm	ASTM D5185(m)	>330	2	2	2
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Antimony	ppm	ASTM D5185(m)		0	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		4	2	5
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		62	63	60
Manganese	ppm	ASTM D5185(m)		<1	<1	<1
Magnesium	ppm	ASTM D5185(m)		1019	1010	982
Calcium	ppm	ASTM D5185(m)		1107	1122	1125
Phosphorus	ppm	ASTM D5185(m)		1113	1097	1070
Zinc	ppm	ASTM D5185(m)		1250	1219	1219
Sulfur	ppm	ASTM D5185(m)		2539	2574	2503
Lithium	ppm	ASTM D5185(m)		<1	<1	<1


CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	4	3	3
Sodium	ppm	ASTM D5185(m)		7	8	9
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>6	0.1	0.1	0
Nitration	Abs/cm	ASTM D7624*	>20	9.4	9.5	9.6
Sulfation	Abs/.1mm	ASTM D7415*	>30	22.5	20.6	22.2

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	>25	18.9	18.5	19.6











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	14.1	14.5	14.3

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0809092
Lab Number : 02580289
Unique Number : 5633349
Test Package : MOB 1

CITY OF PETERBOROUGH
 791 WEBBER AVENUE., MUNICIPAL OPERATIONS CENTRE
 PETERBOROUGH, ON
 CA K9J 8N3
 Contact: Frank Curran
 fcurran@peterborough.ca
 T: (705)742-7777
 F: (705)743-3223

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.